

PRODUCT DATA SHEET



PDS No: 1004

Product Details

Product Code: EZIB101S
Product Name: Ezicover Acrylic Sealer Undercoat
Other Name(s): Not Applicable

Description

Ezicover Acrylic Sealer Undercoat is a premium quality, easy sanding, fast drying, general purpose, acrylic undercoat designed for use on a variety of interior surfaces.

Uses- Suitable for new paper-faced plasterboard, MDF(custom wood) & interior timber.

Features and Benefits

- Easy application, easy sanding
- Excellent adhesion to properly prepared surfaces
- Good coverage/hiding power
- Excellent hold-out
- Ideal for new paper-faced plasterboard walls and ceilings
- Imparts even porosity to the surface
- Low splatter
- Low VOC
- Contains dry film mould inhibitors

Limitations and Precautions

- **Not** recommended for wet areas
- **Do Not** apply when the surface temperature is below 10°C or above 35°C
- Check the weather forecast. **Do Not** apply if rain, heavy dew or a sudden drop in temperature is likely during application or during the first 12 hours after application
- **Do Not** apply if humidity is 85% or above
- Some surfaces may require the use of an oil based sealer or primer. E.g. discoloured or very aged previously painted surfaces or aged unpainted paper-faced plasterboard. A test application should be done first to ensure proper adhesion.

PRODUCT DATA SHEET

PDS No: 1004

Physical Properties

Resin Type	Styrene-Acrylic Emulsion
Pigmentation	Titanium Dioxide and Inert Extenders
Colour	White (can be custom tinted)
Gloss at 60° head	Not applicable
Specific Gravity(Kg/Ltr)	1.47-1.57
Coverage (m²/Ltr)	10-12
No. of coats	One/Two
Dry Times(at 20°C and 60%RH)*	30 min
*(cooler temperatures, higher film thickness and higher humidity can extend the drying and subsequently the recoat time)	
Recoat time	2 hrs
Flash Point	Not applicable
Packaging Sizes	10L,4L,1L
Thinner and cleanup	Water(Upto 10% thinning when spraying depending on weather conditions)
Theoretical VOC(g/Ltr)	Not available

Surface Preparation

Remove all dirt, dust, grease, mould or any other form of contamination from the surface. Use **APCO BIOWash(SDS 9009)** as a moss and mould remover.

Fill cracks and imperfections with a suitable filler and spot prime

Previously painted surfaces should be sanded with 180-220 grit sandpaper(depending on surface condition), to remove loose or flaking paint and to reduce the previous film to a flat finish.

Undercoat Requirements

Not applicable

Application and Process

Stir the contents thoroughly before and during use

Apply one liberal coat then sand smooth before applying topcoats

Apply by brush, roller or spray

For Best Results

- The use of an 8 – 10mm nap roller is recommended
- Allow a minimum of 2 hours prior to sanding and top-coating
- If over-coating with a dark colour, then **Ezicover Acrylic Sealer Undercoat** should be tinted to assist coverage from the top coat.

PRODUCT DATA SHEET

PDS No: 1004

Health and Safety

- Please refer to Safety Data Sheet **(1003)** before use
- Use in well ventilated areas
- **First Aid:**
 - Eyes and Skin irritation – Wash with large amounts of fresh running water
 - If swallowed – drink 2-3 glasses of water and seek appropriate medical advice

Storage

Store in cool, well ventilated areas away from direct sunlight. Keep containers tightly sealed.

Spillage and Disposal

Use rags or sawdust to contain any spill and then dispose of through a commercial waste disposal organisation.

*Please refer to the updated versions of Safety data sheet(SDS) and Technical Data sheet (TDS) before using any **APCO** Product.*

KEEP OUT OF REACH OF CHILDREN

APCO Coatings (NZ) Limited

Ph. (09) 2733 041. Fax. (09) 2733 045. Physical Add. 14 Ron Driver Place, East Tamaki, Auckland 2013

The information and recommendations set down here in this document are presented in good faith and believed to be correct, APCO Coatings (NZ) Ltd gives no guarantee to the completeness and accuracy thereof.

APCO Coatings (NZ) Ltd is not be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the Technical Data Sheet refers.