

ezi•cover Alkyd Enamel

Description:

High Gloss and Semi Gloss: A premium quality Alkyd based Enamel with a smooth, hard wearing finish eminently suitable for doors, walls and ceilings in kitchen, bathroom and laundry areas.

Flat: A professional quality, high opacity alkyd based flat enamel with a durable finish. The product provides easy maintenance of surfaces in steam and moisture prone areas. Ideally suited for ceilings and broad walls in well lit living areas.

Features and Benefits:

High Gloss and Semi Gloss:

- Excellent adhesion to properly primed and undercoated surfaces.
- Resistant to most household chemicals.
- Suitable for primed wrought iron furniture and rails.

Flat:

- Excellent adhesion to properly primed and undercoated surfaces.
- Dries to a smooth, durable flat finish.
- Suitable for all types of ceilings.

Limitations:

Do not apply when ambient temperature is below 10°C.

Provide adequate ventilation during use.

In normal conditions allow seven days for full curing and chemical resistance to develop.

Technical Data:

Resin Type:	Long Oil Alkyd resin
Solvents:	White Spirit
Colour:	Super White
60° Gloss:	High Gloss 92–95% Semi Gloss 35–40% Flat 5%
Density:	1.10-1.30 Kgs/ Litre
Dry-Time:	4 hr touch dry, 16 hr overcoat
Coverage:	14 – 16 m ² per litre (dep on porosity)
Packaging sizes:	4 and 10 litre
Flash Point:	38°C – Flammable
Thinner:	White Spirit or Mineral Turps
VOC:	HG: 345 g/l SG: 373 g/l Flat: 435 g/l

Surface Preparation:

Remove all dust, dirt and grease from the surface. If mould or fungi is present wash surface with APCO Biowash and rinse clean. Apply primer, fill all nail holes and cracks with suitable filler and sand smooth using 220 mesh sand paper, then apply undercoat followed by light sanding prior to application of enamel

Application:

Stir contents thoroughly before and occasionally during use. Apply by brush, roller or airless spray uniformly, after proper surface preparation. Ezicover Alkyd Primer Undercoat is recommended prior to application of topcoat. On aluminium and galvanised steel, use APCO Metacare Etch Primer after light sanding and cleaning. On wrought iron and steel use Apcolite Antirust Metal Primer or Metacare Etch Primer after thorough sanding and cleaning.

For Best Results:

- 1) Apply the product at the one time evenly to the entire area.
- 2) Do not thin for brushing or rolling.
- 4) Allow a minimum of 16 hours drying prior to overcoating.

Health and Safety: (Please refer to Material Safety Data Sheet before using)

Ezicover Alkyd Enamel is essentially **flammable – keep away from naked flame, DG Class 3.2, UN No. 1263, P.G. III**, but non-toxic. Does not contain any added toxic heavy metals such as lead, mercury etc. Provide plenty of ventilation and avoid breathing vapours.

KEEP OUT OF REACH OF CHILDREN



0800 BUY APCO
Ph. 09) 2733 041
Fax. 09) 2733 045

PO Box 58849
Botany
Manukau 2163

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, APCO Coatings NZ Ltd makes no representation as to the completeness and accuracy thereof.

In no event will APCO Coatings NZ Ltd be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers

Page 2 of 2 Pages 10/10/2013