

TECHNICAL DATA SHEET

AGGRETEx H



DESCRIPTION



Harris Aggretex H is a concrete surface retarder that is especially formulated as a light brown low viscosity liquid. It is sprayed on the horizontal trowelled surface of wet concrete to delay the setting time at the surface.

The surface film of cement paste may then be later washed or brushed away, leaving the aggregate exposed to form an attractive, textured surface.

TYPICAL USES

- Textured wet concrete on horizontal surfaces
- Pavements
- Driveways

DIRECTIONS FOR USE

Application:

Stir thoroughly before use. Spray application should take place as soon as compaction and finishing of the concrete surface has been completed, at a rate of 7-15m² per litre (275-600ft² per gallon). Hot weather will reduce the retardation period. Aggretex H film should be protected from rain or other damage. To achieve the desired finish, the treated concrete surface should be brushed/ washed within 3-12 hours at 30°C. Temperature variations will affect this time period, so allowance should be made when operation in different ambient conditions.

NOTE: Depending on actual requirements, field trials should be conducted with the specific cements and mix designs in use to determine the optimum depth of penetration of Aggretex H vs coverage rate.

Clean up with water.

COMPOSITION

An aqueous polysaccharide solution with preservatives.

TECHNICAL DATA SHEET

AGGRETEX H



PACKAGING SIZES

Available in Five Gallon (18.92 Litres)

PRECAUTIONS

KEEP OUT OF REACH OF CHILDREN

READ DIRECTIONS CAREFULLY BEFORE USE:

SAFETY DIRECTIONS

CAUTION

NON- FLAMMABLE

Best stored under cool conditions.

Dispose of in accordance with local regulations

FIRST AID

If in contact with eyes, rinse immediately with plenty of water and seek medical advice. If in contact with skin, wash immediately with water. DO NOT SWALLOW. If ingested, do not induce vomiting, drink water and obtain medical attention.

TECHNICAL ASSISTANCE

For advice and recommendation on the use of all Harris/BH Paints and Building Products, consult the Harris Technical Department, Tel: (246) 429-4840.

Email: technical@harrispaintsonline.com