



**Sri Trang Agro-Industry Public Company Limited**

No. 10 Soi 10 Phetkasem Road, Hatyai, Hatyai Songkhla 90110 Thailand

Tel. +66 7434 4663 Fax. +66 7434 4677

TAX IDENTIFICATION NUMBER 0107536001656

**Certificate of Analysis**

Cosignee : KM Healthcare  
 Type of Gloves : Nitrile Examination Gloves Powder Free

Date : 16<sup>th</sup> Jun 2018  
 Invoice No. : 5001054914  
 Order No. : KMH18-323

Test Performed	Standard ASTM D 6319	Results	
Inspection Plan ISO 2859 Watertight Failures(1000 ml) GI AQL 1.5	7/8 (AC/RJ)	XS	-
		S	-
		M	0
		L	-
Dimension Length S2 AQL 4.0	Min 220	XS	- mm
	Min 220	S	- mm
	Min 230	M	239 mm
	Min 230	L	- mm
Width	70±10	XS	- mm
	80±10	S	- mm
	95±10	M	95 mm
	110±10	L	- mm
Thickness (Single wall) Finger	Min 0.05	XS	- mm
		S	- mm
		M	0.08 mm
		L	- mm
	Min - Max : 0.05 - 0.07	XS	- mm
		S	- mm
		M	0.06 mm
		L	- mm
	Max : 0.07	XS	- mm
		S	- mm
		M	0.06 mm
		L	- mm
<b>Physical properties S2 AQL 4.0, before aging</b>			
Tensile Strength (min)	14 Mpa	XS	- Mpa
		S	- Mpa
		M	48 Mpa
		L	- Mpa
Elongation at break (min)	500%	XS	- %
		S	- %
		M	645 %
		L	- %
<b>Physical properties S2 AQL 4.0, after aging</b>			
Tensile Strength (min)	14 Mpa	XS	- Mpa
		S	- Mpa
		M	48 Mpa
		L	- Mpa
Elongation at break (min)	400%	XS	- %
		S	- %
		M	537 %
		L	- %

\*Accelerated aging carried out as per ASTM D 3577 at 70 °C for 168 hours

\*The inspection plan is following according to ISO 2859, GI AQL 1.5 (Watertight test), S2 AQL 4 (others)

Protein content	N/A	N/A	
Powder content	Test Standard ASTM D 6124	XS	- mg/g
		S	- mg/g
		M	0.03 mg/g
		L	- mg/g
Sterilization Method	N/A	N/A	

Lot no.

M 052018 2555

Panjanat

Assistant Product Manager