



Part number: ELE-ER34615-BAK

Bobbin Cell

Primary Lithium Battery

ER34615 3.6V




3.6V Primary lithium-thionyl chloride (Li-SOCI2) Energy Typ^

For low drain/long term operating applications requesting superior voltage response in -55°C \sim +85°C environments

Cell size references	l	<u>JM1-R20-D</u>
Alternative models	LS33600/LST33600/LS33600C/	<u> TL4930/TL5930</u>
Electrical characteristics (Typical values relative to cells stored for one ye Nominal capacity (At 3mA +20°C,2.0V cut off.The capacity restore		19Ah erature,cut off)
Open circuit voltage(At 20°C)		3.66V
<u>Nominal voltage (At 3mA +20°C)</u>		3.6 V
<u>Max. continuous current (at +20°C)</u>		200mA
<u>Typical Max. Pulse current (at +20°C)</u>		400mA
Pulse capability:Typically up to 400mA (400mA/0.1second pulses drained every 2min at 20°C from cells with 50µA base current, yield voltage readings above 3.0V.The readings may vary according to pulse characteristics, temperature and cell's previous history.Fitting the cell with a capacitor may be recommended in severe conditions.Consult ACT if necessary)		
Storage (recommended)		+30°CMax
Operating temperature range (High and low temperature will lower the capacity Physical characteristics	ty and load voltage.)	<u>-55°C~+85°C</u>
<u>Diameter(Max)</u> Height(Max) Typical weight Available terminal suffix	radial tabs, radial pins, axial le	<u>34mm</u> <u>61.5mm</u> 99g ads,flying leads





Key features

- >High and stable load voltage
- >Superior drain capacity
- >Low self-discharge rate
- (less than 1% after 1 year of storage at 20°C)
- >Stainless steel container
- >Hermetic glass-to-metal sealing
- >Laser welding
- >Non-flammable electrolyte

Main applications

- >Radiocommunication and other military applications
- >Alarms and security systems
- >Beacons and emergency location transmitters
- >GPS equipment
- >Metering systems
- >Led lighting applications
- >Others

Storage

- >Cells should be stored in a clean &dry(less than 30% RH) area >Temp. should not exceed +30°C

Warning

- >Do not use if cell casing is mangled >Do not use different model of cell in series
- >Soldering the tag should be finished in few seconds
- >Do not try to recharge

