

# buro

ergonomics at work®

---

**buroseating**

 **Konfurb**

**mondo**

---

Upholstery Collection

**Buro New Zealand**


**Buro Jett Fabric**




**Black**  
63




**Dark Blue**  
61



**Charcoal**  
62




**Green**  
64



**Red**  
66

**Elastic III**



**Black**  
153

**Zen**



**Black**  
103

**Spice**



**Black**  
13

**Buro SafeTex - Anti-Bacterial (Indent)**



**Charcoal**  
8106

**CULP Dorset**



**Grey**  
82

**Dillon PU - Anti-Microbial**



**Black**  
PU13




**Williamsburg Blue**  
PU11

**Gin Rummy**




**Gravel**  
67


**Roy Mesh**



**Black**  
X1-108



**Red**  
X1-101



**Blue**  
X1-106


**Yuna Fabric**




**Grey**  
Y2263-008



**Black**  
Y2263-004




**Green**  
Y2263-001




**Orange**  
Y2263-007

**Lane Mesh**



**Black**  
LN04




**Grey**  
LN02

**Keylargo**




**Ash**  
122

**Leather**



**Black**  
L3

**Vinyl**



**Black**  
V3

**PU**



**Black**  
PU3

**Air Mesh**



**Black**  
AM3

**Noir**



**Black**  
03

**Diablo Fabric Mesh**



**Charcoal**  
CI-13

	Fabric Content	Width (cm)	Tensile Strength	Tearing Strength	Abrasion Resistance	Flame Resistance	Colour Fastness
<b>Jett</b>	100% Polyester	152	Warp: 355.7 Weft: 362.4	Warp: 24.4 lbs Weft: 25.1 lbs	Martindale Over 50,000 rubs	CA TB 117	4.5
<b>Elastic III</b>	100% Polyester	152	—	—	Martindale Over 30,000 rubs	CA TB 117	4
<b>Zen</b>	100% Polyester	152	—	—	Martindale Over 50,000 rubs	CA TB 117	—
<b>Spice</b>	100% Polyester	152	—	Warp: 52.0 lbf Weft: 46.5 lbf	Martindale Over 75,000 rubs	CA TB 117	4
<b>Leather</b>	Leather	—	—	102.1 N	—	—	4
<b>Vinyl</b>	PVC	140	349.9/117.6	32.3/25.5	Wyzenbeek 100,000 cycles	CA TB 117	—
<b>Diablo Fabric Mesh</b>	Nylon 49.1% Polyelastomeric 50.9%	162	Warp: exceeds 287.5 lbf Weft: exceeds 449.4 lbf	—	Martindale over 100,000 rubs	CA TB 117	4.5
<b>PU</b>	15% Polyurethane (PU), 40% PVC, 45% Fabric Backing	137	Warp: 59.42 kg Fill: 61.87 kg	—	Martindale over 30,000 rubs	CA TB 117	4-5
<b>Dillon PU (Anti-Microbial) With 'Silver Ion'</b>	100% Polyurethane	142	Warp: 101 Fill: 96	Warp: 17 Fill: 13	Wyzenbeek exceeds 200,000 cycles	CA TB 117-2013	Wet - Class 4 Dry - Class 4
<b>SafeTex - Indent (Anti-Bacterial)</b>	100% Polyester	150	—	Warp: 23.4 lbs Weft: 16.2 lbs	ASTM D4157-2013(R17) Over 60,000 rubs	—	Wet - Class 4.5 Dry - Class 4.5
<b>Roy Mesh</b>	100% Polyester	160	—	—	Martindale 100,000 rubs EN ISO 12947-2	CA TB 117-2013 sec1 Pass	ISO 105E01-2013 4.5
<b>Air Mesh</b>	100% Polyester Mesh	147	—	—	Wyzenbeek 30,000 rubs	CA TB 117 Section E Class 1	Wet - Class 4 Dry - Class 4
<b>Yuna</b>	100% Polyester	150	—	—	Martindale 100,000 rubs ASTMD4157-2013	CA TB 117-2013 sec1 Pass	ISO 105X12-2001 4.5
<b>Lane Mesh</b>	Nylon 40.3% Polyester 59.7%	160	—	—	Martindale 100,000 rubs ASTMD4966-2012	—	AATCC8-2013 4.5
<b>Key Largo (Warwick)</b>	100% Polyester	140	—	—	Martindale 160,000 cycles	Visit Warwick website for full test results	Dry - 5.0 Wet - 5.0
<b>Gin Rummy (Culp)</b>	100% Polyester	138 (+/- 2 cm)	135	—	Wyzenbeek 30,000 rubs	CA TB 117	Dry - 4.0 Wet - 4.0
<b>Noir</b>	100% Polyester	150 (+/- 2 cm)	—	—	Wyzenbeek 30,000 rubs	CA TB 117	Dry - 4.0 Wet - 4.5
<b>CULP Dorset With 'i-Clean'</b>	100% Polyester	138 (+/- 2 cm)	130	—	Wyzenbeek 55,000 rubs	CA TB 117-2013	Dry - 4.0 Wet - 3.0