




Type EWT-PA split-flex




Product information

The EWT-PA cable protection conduits are made of specially modified polyamide 6. The material is halogen, phosphor and cadmium-free. The conduits are suitable for static applications involving light to medium mechanical loads.

The EWT-PA cable protection conduits consist of a two-piece slotted conduit system and feature the following advantages:

- Cable protection conduits can be opened and closed at any time.
- Mounting of pre-assembled cables
- Retrofitting or repair in mechanical and plant engineering

Color: Black





Information, conformities and approvals



Article	Order No.	A Ø mm	B Ø mm	R stat. mm	Weight kg/100m	PU m
EWT-PA-M10/P7	83164250	5.7	11.5	70	3.7	50
EWT-PA-M12/P9	83164252	7.9	12.9	75	4.6	50
EWT-PA-M16/P11	83164254	10	16.2	100	6.0	50
EWT-PA-M20/P16	83164256	13.7	21	120	11.0	50
EWT-PA-M25/P21	83164258	19.8	28.4	170	16.6	50
EWT-PA-M32/P29	83164260	25	34.2	180	21.0	25
EWT-PA-M40/P36	83164262	32.3	43.5	200	29.3	25
EWT-PA-M50/P48	83164264	44	53.3	240	40.0	25
EWT-PA-70 Jumbo	83261022	62.2	79	300	53.0	10





Type EWT-PA split-flex

Material properties **Thermal properties** Temperature / temperature range -40 °C – 120 °C 4 mod. polyamide PA 6 short termshort term: 160 °C High angle consistency >900 N Ac-Â cording to IEC EN 61386 M25/P21 Flexural fatigue strength >15000 ~ According to IEC EN 61386 **Chemical resistance Fire properties** Fire classification acc. to Resistant to: Alcohol, Mi-UL94: HB neral oils, Greases, Fuels **Technical information** Conformity **RoHS (EC Directive** HF Halogen-free 2011/65/EU) **General information** Approvals and operating permits ECOLAB approval Made in Germany

All details given in our sales brochures and catalogues, as well as the information available online, are based on our current knowledge of the products described. The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the products described. A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information. All information with respect to the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge. They do not release the buyer from the obligation to carry out his own tests and trials in order to determine the concrete suitability of the products for the intended purpose. Murrplastik accepts no sponsibility for the available information heing up-to-date, correct or complete. Neither do we accept responsibility of the guality of this information. Murrplastik accepts no liability for damage caused as a result of using our products. Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services. Our General Terms and Conditions apply.