


EasyPuff[®] Metallic

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certification
PU	180 Microns	Adhesive Polyester	

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	100 gf	30cm/sec	10+10 Seconds	140°	Medium (5 Bar)	warm/hot

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Press for 10 seconds at 140°, remove carrier, cover & press for further 10 seconds

PRODUCT HIGHLIGHTS

- Heat transfer vinyl that expands after pressing to create a 3D effect with a shiny finish
- Unique look with a gold or silver sheen

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble Dry	Dry Cleaning	Storage Shelf Life	Storage Temperature	Conditions	Position
Cold wash inside out, with mild detergent	YES Inside-out	YES Low setting	NO	Up to 2 years	Between 18-26° C	Away from sunlight & dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations.

