



## PRODUCT SPECIFICATIONS – Reflective

### Euro Reflective

#### **Application instructions (home iron)**

- Set iron dial between Cotton and Linen
- Cover design with Baking Paper or non-stick cover sheet
- Place on flat, hard surface (ironing board not recommended)
- Press iron with medium/firm pressure (do not slide iron)
- Press each section of design for 8 - 10 seconds
- If areas of design lift after application, replace cover sheet and re-press for 5 seconds
- Peel carrier warm

#### **Application Instructions (heat press)**

- Preheat garment for 2-3 seconds
- Apply design at 140°C - 145°C
- Use medium pressure for 8 - 10 seconds
- Peel carrier warm

Wait at least 24 hours before washing

### Thermoflex Reflective

#### **Black**

Pre-heat fabric for 2 - 3 seconds  
150 - 160 degrees  
8 - 10 seconds  
Medium Pressure  
Peel warm

#### **Silver**

Pre-heat fabric for 2 - 3 seconds  
160 degrees  
15 seconds  
Medium Pressure  
Peel warm