

THE VINYL LOFT

PRODUCT SPECIFICATIONS

THERMOFLEX PLUS

Application Instructions (heat press)

- Preheat garment for 2 - 3 seconds
- Apply design at 160°C
- Use medium pressure for 15 seconds, remove carrier and repress for 2 seconds
- Peel carrier warm (Neon colours – peel luke warm) Wait at least 24 hours before washing

Suitable for use on cotton, polyester, and polycotton blends, acrylic



45° Blade
Recommended



Cut this material in
mirror image



160°C -165°C



2,0 - 3,0 bar
Medium/pressure



15 Seconds



Peel Warm, except
for Neon Colours –
peel luke warm



Wash warm (max
80°C) inside out.
Gentle cycle. Tumble
Dry Normal



Can be layered



Iron inside out. Do
not iron directly
onto transfers.



Suitable for cotton,
polyester and
polycotton blends



Application Tape not
required.