

PROVISIONAL PRODUCT DATA SHEET 2019-05-17

Rollbase Polyester-V

PLASTOMERIC MODIFIED BITUMINOUS MEMBRANE TO BE USED AS SEPARATION LAYER

DESCRIPTION

Rollbase Polyester-V is an APP modified bituminous membrane to be nailed on the substrate and used as a base for torch adhesion of other sheets when you cannot do it directly to the substrate, such as timber or metal. The underside is coated with an exposed non-woven polyester fabric, which is absorbent and traps the remaining humidity from wooden substrates or old waterproofing membranes. It is reinforced with a fiberglass to ensure the dimensional stability. The top surface finish: polyethylene film. Weight: 2,0 kg/m²

USES

Roof waterproofing accessory for:

- Flat and sloped roofs as a base for torch adhesion of bituminous membranes and/or as humidity diffusion.

CHARACTERISTICS / ADVANTAGES

- Several methods of application: mechanically fixed, torch applied, hot welded or with cold adhesive and hot melt bitumen
- Good tear resistance
- High mechanical properties
- Good elongation and cold flexibility

PRODUCT INFORMATION

Composition	APP modified bitumen	
Packaging	Roll size	
	Length	10,00 m
	Width	1,05 m
Appearance / Colour	Top surface	Polyethylene film
	Backing	Non-woven polyester fabric
Shelf life	36 months from date of production	

Storage conditions	Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.		
Length	10,00 m - 1 %		
Width	1,05 m - 1 %		
Mass per unit area	2,0 kg/m ² ± 0,2 %		
Tensile Strength	Longitudinal	700 N/50mm ± 20 %	(EN12311-1)
	Transversal	400 N/50 mm ± 20 %	
Elongation	Longitudinal	50 % ± 15 %	(EN12311-1)
	Transversal	20 % ± 15 %	
Resistance to Tear	Longitudinal	120 N ± 30 %	(EN12310-1)
	Transversal	120 N ± 30 %	
Water Vapour Transmission	μ = 100.000 ± 20 %		(EN 1931)
Watertightness	60 kPa		(EN 1928-Method A)
Flow Rate	≥ 100 °C		(EN 1110)
Ambient Air Temperature	+5 °C min. / +50 °C max.		
Substrate Temperature	+5 °C min. / +50 °C max.		

SUBSTRATE QUALITY

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the waterproofing build-up. When used as a roofing membrane, the complete roof system must be designed and secured against wind uplift loadings. The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loosely adhering particles.

SUBSTRATE PREPARATION

Use the appropriate preparation equipment to achieve the required substrate quality.

APPLICATION METHOD / TOOLS

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Alignment

Unroll, align and re-roll correctly before torching.

Overlaps

- Side: 100 mm
- End: 150 mm

Fastening

Rollbase Polyester-V can be mechanically fixed on the substrate by using large-headed fasteners. Contact Sika Technical Services for additional information.

Torching

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the

backing film starts to melt, the membrane is ready to stick.

Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

Hot Bitumen or Cold Adhesive bonding.

Refer to the individual Product Data Sheets.

Detailing

All details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc. must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for torch-applied membranes.

Protection

The membrane must be protected from damage during any ongoing site activities.

IMPORTANT CONSIDERATIONS

- At low temperatures, take care unrolling to avoid damaging the membrane.
- Use suitable footwear to avoid puncturing the membrane.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at +260 °C) will be damaged making the membrane un-useable.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps. If this occurs, un-bonded areas must be lifted and re-torched.
- If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Services AG

Tüffenwies 16
8048 Zürich
Tel: +41 58 436 4040
www.sika.com



PROVISIONAL_RollbasePolyester-V-en-(05-2019)-1.pdf

PROVISIONAL PRODUCT DATA SHEET 2019-05-17
Rollbase Polyester-V
May 2019, Version 01.0
020945139000000002

BUILDING TRUST

