



MUSEUM Services Corporation
385 BRIDGEPOINT WAY
SOUTH ST. PAUL, MN 55075 USA
Telephone 651/450-8954 Facsimile 651/554-9217

AN ART CONSERVATION EQUIPMENT COMPANY

EQUIPMENT, SUPPLIES, AND SERVICES FOR INSTITUTIONS AND INDIVIDUALS

Instructions for the Use of BEVA ® 371 Solution

All work with BEVA adhesives should be performed in a well-ventilated room.

Preparation of the Adhesive

Open the can of BEVA 371 Solution. Remove about one pint (about 500 ml) of solution and add to one pint (about 500 ml) of VM&P Naphtha/Xylenes. The VM&P Naphtha/Xylenes component can be all Naphtha (faster drying), all Xylenes (slower drying), or a mixture of both to make a 37S solution. Cover the can but do not seal.

Warm the solution mixture in a double boiler until solution is clear. Solution should be of a thin, liquid consistency. Stir occasionally.

In this form, BEVA 371 Solution is the standard adhesive for lining and can be applied to both the old canvas and the new support. The most suitable manner of application is with a medium nap paint roller. Apply with roller as if applying paint. Roll the roller in the BEVA 371 solution and allow to drain slightly before applying to the work surface.

When through, the excess BEVA 371 Solution in the roller may be squeegeed back, into the storage can, the roller removed from its holder, and immersed in a well-covered jar of Naphtha until needed again. If frequently used, the roller may be kept moist and pliable by wrapping it in thin Mylar. There is virtually no waste, as even the contents of the storage jar can later be used for facings.

Preparation of the painting

The painting is prepared for lining, as might be required in each case, performing one or all of the following operations, usually in the order listed below:

- a. "Face" painting, if necessary.
- b. Remove painting from stretcher and flatten tacking edges.
- c. Reattach loose paint (if necessary, consolidate entire painting) using BEVA (1) or another preferred method.
- d. Join the tears, fill losses (2). If losses were badly filled before, the old varnish must be removed and fillings corrected.
- e. Revarnish painting for protection.
- f. Place painting, face-down, on a board covered with silicone coated paper or film. Tape tacking edges to the board so painting will not move. Level the back of the painting carefully with a scalpel, shaving off all protruding knots, burls or ridges of a canvas weave. Do not sand. Remove all loose glue.
- g. Correct deformations in the plane of the painting by vapor-treatment.
- h. Depending on desired degree of penetration, either coat the back of the painting with BEVA or spray with an 8-10% solution of BEVA in Naphtha and/or Toluene (1:3 or 1:4). Allow to dry overnight.

It is best to perform all operations with BEVA at the end of the day so as not to remain exposed to solvent fumes for too long.

Preparation of the Lining Fabrics

Some of the steps in the preparation of the painting require time to dry. These pauses may be used to prime the lining fabrics with a spray-coating of either BEVA 371 or BEVA D-8.

Berger used the following lining laminate:

- A sandwich layer of fine, flexible Dacron-polyester (the finer and more regular the weave, the better).
- A Mylar/polyester film interleaf (optional).
- A backing fabric.

While the Sandwich layer and the backing fabric may be prepared in large sheets well ahead of time, stored indefinitely, and cut to size when needed, the polyester film interleaf should be made as the very last step before the actual lining.

Preparation of the Sandwich Layer and the Backing Fabric

The fine Polyester fabric is lightly tacked to a large strainer and sprayed with a thinned solution of BEVA 371 or BEVA D-8 from both sides, then left to dry.

The backing fabric is prepared in a similar fashion, except that spraying with BEVA is done on one side only, the side which will be attached to the laminate.

Preparation of the Interleaf

A piece of heavy Mylar (5-7.5 mil thick) is cut about 2-3 inches larger than the painting to serve as an interleaf. It provides the lining with sufficient stiffness to resist deformation and forms a good moisture barrier.

The cut piece is lightly tacked to a board, covered with silicone-coated paper or film. The interleaf is coated with a continuous coat of BEVA 371. Since polyester film does not absorb any BEVA, this coat dries in about 15 minutes. The polyester film is then inverted, and its reverse also coated with BEVA 371.

The dry polyester film is placed on a carefully cleaned cardboard.

The painting is placed on top of it, "face-up." The outline of the painting is marked on the polyester film with a fine felt-tip pen.

The painting is removed, and an additional line is marked within the outline, about 1/8" inside the border.

The interleaf is cut along the inside line to be slightly smaller than the painting. Because paintings are often irregular, it is better to cut the mylar with scissors. This should be done immediately preceding lining, in order to prevent contamination of the polyester film.

Assembling the Laminate

The Vacuum Hot Table should be carefully cleaned. The Vacuum Hot Table can accentuate every unevenness, be it on the table or within the laminate. Therefore, each layer of the laminate must be carefully inspected for any impurities before being put on for the lining.

The following steps are to be taken:

- Cover the table with a sheet of polyester film about 1-1.5 mils thick. This should be used instead of silicone-coated paper, which seldom lies flat on the Vacuum Hot Table (experienced practitioners can easily dispense with this step, since there is practically no danger for the BEVA penetrating the backing fabric if properly prepared).

- Place backing fabric on the polyester film or Vacuum Hot Table, with the side which was sprayed with BEVA facing up.
- Put dry, precut interleaf on top of the backing fabric, and align carefully with the threads of the backing fabric.
- With a tacking iron, press down lightly on two adjacent corners of the interleaf to the backing fabric to make sure it will stay in the aligned position.
- Put sandwich layer on top of the interleaf. With a pencil or chalk, mark the continuation of the outlines of the interleaf on the sandwich layer. Starting from the center, smoothen it lightly with both hands.
- While the painting is still on a board, cut the four corners of the tacking margins, so that the painting can be aligned within the outlines marked on the sandwich layer (if trimming of the tacking margins is unacceptable, register marks can easily be drawn to show the exact position of the corners).
- Place painting on the sandwich layer 'face-up' and align it with the help of the register marks. Press down lightly to attach the layers in perfect alignment.
- Put "breathers" around the edges of the painting.
- Cover laminate with the membrane and evacuate the air.
- Do not start heating the table immediately. This permits checking the laminate once more, this time under pressure. It also assures better evacuation of the air which might otherwise be hampered once the different layers fuse together.
- Heat table until surface temperature of the painting reaches 150 degrees F (65 degrees C) in all parts of the painting. At least five paper thermometers should be used for reach thermal blanket heating the table, one each corner and one in the center. Do not rely on electronic thermometers alone.
- Allow to cool slowly, under pressure, to at least 85-90 degrees F. The latest stress measurements carried out by Russel and Berger have shown rapid cooling to be stressful to paintings.

Please, note that the assembly of fabrics in the above described laminate have been worked out to alternate a porous layer with a non-porous one in order to assure a good evacuation of air and a proper distribution of pressure within the laminate. This permits lowering the vacuum pressure to a minimum, although a stronger vacuum often assures a better looking lining. Also note that with the above arrangement the use of a membrane is not absolutely required. Consequently, the vacuum can be arranged to join the layers of the laminate without applying pressure to the face of the painting. In addition, alternating porous and non-porous layers facilitates the reversibility of the laminate.

Miscellaneous Uses

Facings: Thin BEVA 371 with VM&P Naphtha (1:1). Because BEVA will stick to a wet surface, wet-strength tissue may be placed in the usual manner for a facing, and wetted and tamped into the most rough surface with a soft brush. The BEVA facing mixture can then be rolled or brushed immediately over the wet facing. Do not go over areas of drying BEVA a second time, the facing may lift. Process as required on hot table between sheets of silicone paper, when dry.

Blisters: Prepare a mixture of BEVA 1:4 or 1:3 with VM&P Naphtha. This may be flowed into the cracks and crevices of the paint or injected under the paint layer while warm. Let dry 24 hours, cover with a small piece of silicone paper and flatten with a tacking iron. Blisters may be faced if required.

Removal of Facings: Spray or flow VM&P Naphtha over sections about one foot square at a time, cover with a piece of polyester film and warm slightly for two to three minutes. Facing will then peel directly off. Alternate method, cover faced painting with a piece of newspaper (one foot square) and wet well with Naphtha. Proceed as above. Facing should peel off attached to the newspaper. Clean face of the painting with Naphtha, removing all traces of the BEVA.

Vapor Treatment: To flatten heavily cupped or deformed paint films, vapor treatment is best performed before BEVA is applied. This treatment is not without hazard and requires extensive study and experience (1,2,3).

Fixing Minor Flakes: Lightly transfer 1:3 BEVA Naphtha mixture, preferably warm, from point of brush to edges of flaked paint. It will immediately draw around and under flakes. Cover with facing paper and press down to remove excess BEVA which might form a ridge under the paint. This precaution is important in interlayer delamination or on non-absorbing grounds. Allow to dry 24 hours. Cover with a piece of silicone paper and flatten with tacking iron.

IMPORTANT NOTE: It is imperative to employ silicone paper above and below all work whether linings or small tacking jobs. BEVA will stick to Teflon coated irons, polyester film, and everything else. NEVER use BEVA directly when mounting a painting on any hard, inflexible support. ALWAYS put a piece of fine fabric on the solid support first.

Removal of a BEVA Lining: To remove a BEVA lining, place the painting on the Vacuum Hot Table and apply by brush or spray VM&P Naphtha to the back of the lining. Cover with a sheet of polyester film. The Vacuum Hot Table should be preheated to about 120 degrees F. Wait about five minutes and test to see if the lining can be peeled. If not, repeat the above process. When BEVA has been softened to the proper degree, the lining will release without stress to the old canvas. If the painting is large, this may be done in sections.

REFERENCES:

1. G.A. Berger, "Consolidation of Delaminating Paintings", Preprints to the ICOM Meeting in Zagreb (1978).
2. G.A. Berger, "Heat-Seal Lining of a Torn Painting with BEVA 371", Studies in Conservation, 20, No. 3 (1975),
3. G.A. Berger, "Unconventional Treatments for Unconventional Paintings", Studies in Conservation, 21, No. 3 (1976).

Museum Services Corporation urges each customer or recipient of this informational sheet to study it carefully and consult appropriate expertise, as necessary or appropriate, to become aware of and understand the data contained in this informational sheet and any hazards associated with the product. The information herein is provided in good faith and believed to be accurate as of the sources shown above. However, no warranty, express or implied, is given. It is the buyer's/user's responsibility to ensure that their activities comply with all federal, state, provincial or local laws. The information presented here pertains only to the product as shipped. Since conditions for use of the product are not under the control of the manufacturer, it is the buyer's/user's duty to determine the conditions necessary for the safe use of this product. Due to the proliferation of sources for information such as manufacturer specific information sheets, we are not and cannot be responsible for information sheets obtained from any other sources. If you have obtained an information sheet from another source or if you are not sure that the information sheet you have is current, please contact us for the most current version.