



# Technical Data Sheet

3M™ Single-Coated Urethane Foam Tape  
4317



[Product Details](#)



[Regulatory Info/SDS](#)

## Product Description

3M™ Single-Coated Foam Tapes will adhere to a variety of substrates, including latex-painted wood, lacquered wood, enameled steel, glass, aluminum, stainless steel, acrylic, ABS, and PVC (non-plasticized) as tape adhesion is typically satisfactory within 20 minutes and continues to build with additional time.

## Product Features

3M™ Urethane Foam Tapes Series 4300 are a conformable, grey, low-density, opencell foam with pressure-sensitive acrylic adhesive on one side. The adhesive is protected by a 0.003 inch (0.08 mm) thick tan, silicone treated paper liner and has a very soft, conformable low density foam which can help seal out air, dust and light when compressed 50%. Application ideas include: recessed lighting, door, window and cabinet seals. It also can be used to help cushion, damp sound and absorb vibration in electronics such as printers, keyboards, computers, aircraft lights and automotive dash boards. This tape is available on individual cores and in blocks of 1.5 inches when the tape is 3/4 inch or less in width. Note: Extra care should be taken when handling these delicate rolls of tape to avoid damaging tape.

## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Physical Properties

Attribute Name	Test Method	Value
Color		Charcoal grey
Adhesive Type		430*
Density	ASTM D3574	32 kg/m <sup>3</sup> (2 lb/ft <sup>3</sup> ) <sup>1</sup>
Shore 00 Hardness	ASTM D2240	6 <sup>1</sup>
Mold and Mildew Resistance	ASTM G21	No growth after 28 days <sup>2</sup>
Compression Deflection: 25% Compression	ASTM D3574	2.1 kPa (0.3 lb/in <sup>2</sup> )

<sup>1</sup> Foam with adhesive

<sup>2</sup> Foam with Adhesive

Attribute Name	Value
Thickness	9.5 mm (375 mil)
Liner Thickness	0.08 mm (3 mil)
Primary Liner Color	Tan
Thickness Tolerance	10 %

Attribute Name	Value
*Note	*3M™ Adhesive 430 is a medium soft adhesive system that offers good quick stick to many types of surfaces along with excellent aging and UV resistance.

## Typical Performance Characteristics

Attribute Name	Value
Short Term Temperature Resistance	121 °C (250 °F) <sup>1</sup>
Long Term Temperature Resistance	66 °C (150 °F) <sup>2</sup>
Temperature Resistance	Cold flex at -29 °C (Cold flex at -20 °F) <sup>3</sup>

<sup>1</sup> Short Term (minutes, hour)

<sup>2</sup> Long Term (day, weeks)

<sup>3</sup> No cracks. Tape slowly bent around a 1/4 in. diameter mandrel.

Attribute Name	Test Method	Value
Elongation	ASTM D3574	125 % <sup>1</sup>
Tensile Strength	ASTM D3574	170 kPa (25 lb/in <sup>2</sup> ) <sup>1</sup>
Compression Set	ASTM D1667	5 %

<sup>1</sup> Die "A"

## Typical Environmental Characteristics

### Solvent Resistance

Solvent/Fuel	3M urethane foam tape series 4100	
	Adhesive	Foam
Acetone	Softens	Softens
Ammonia Cleaner	No effect	No effect
Engine Oil	No effect	No effect
Gasoline	Softens	Swells
JP-4 (jet fuel)	Softens	Swells
MEK	Softens	Softens
Mineral Spirits	No effect	Swells
Soapy Water	No effect	No effect

\*Visual observations of tape bonded to steel panels and immersed totally in solvent/fuel for 24 hours.

## Electrical and Thermal Properties

Attribute Name	Test Method	Value
Thermal Conductivity	ASTM C518	0.043 W/m/K (3 (btu-in)/(h-ft <sup>2</sup> -°F))
Surface Resistivity (Adhesive)	ASTM D257	5 x 10 <sup>12</sup> Ω <sup>1</sup>
Surface Resistivity (Non-Adhesive)	ASTM D257	3 x 10 <sup>12</sup> Ω <sup>2</sup>
Water Absorption: 30% Compression	ASTM D1056	open cell - NA % by Volume

<sup>1</sup> Adhesive Side

<sup>2</sup> Non-Adhesive Side

## Handling/Application Information

### Application Techniques

- Bond strength is dependent upon the amount of adhesive-to-surface contact. Firm application pressure develops better adhesive contact and helps improve bond strength.
- To obtain optimum adhesion, the bonding surface must be clean, dry, and well unified. Some typical surface cleaning solvents are isopropyl alcohol and heptane.\*

\*Be sure to follow the solvent manufacturer's precautions and directions for use when handling solvents.

- Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

## **Storage and Shelf Life**

Store in the original cartons at 60-80°F (15-27°C) and 50% relative humidity.  
Shelf life is 24 months from date of manufacture.

## **Available Sizes**

<b>Attribute Name</b>	<b>Value</b>
Maximum Available Width	1168 mm (46 in)
Maximum Length	8.2 m (9 yd)
Minimum Available Width	9 mm (0.375 in)
Normal Slitting Tolerance	± 0.8 mm (± 1/32 in)
Roll Diameter	508 mm (20 in)
Standard Roll Length	8.2 m (9 yd)

## **Automotive Disclaimer**

**Select Automotive Applications:** This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M  
Industrial Adhesives and Tapes Division  
3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550

3M is a trademark of the 3M Company.  
©3M 2022 (5/22)