



Technical Data Sheet

3M™ Scotch-Weld™ Epoxy Adhesive/Coating 2290



[Product Details](#)



[Regulatory Info/SDS](#)

Product Description

3M™ Scotch-Weld™ Epoxy Adhesive/Coating 2290 is an amber tinted thermosetting adhesive/coating for metal to metal bonding and coating. It can be used to assemble laminated steel cores for electrical motor stators and rotors, to adhere copper foil to B-staged epoxy in the manufacture of printed circuits, and to coat, protect, and utilize coils and electronic subassemblies.

Product Features

- Offers exceptionally high shear and peel strength properties.
- One-part formula; no premixing required.
- Dries to a tack-free film. Bonds can be made up to 3 months later.
- Excellent wetting during cure - only one surface need be coated.
- Requires only sufficient pressure to keep bonded parts dimensionally stable.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Attribute Name	Value
Color	Light Amber ¹
Viscosity	40 to 80 cP
Net Weight	7.2 to 7.6 lb/gal
Base Resin	Epoxy

¹ Colors may vary from nearly white to yellow/amber. Adhesive performance is not affected by color variation.

Typical Physical Properties

Attribute Name	Value
Cured Color	Light Amber
Solids Content by Weight	19.5 to 23 %
Solvent Resistance	Methyl Ethyl Ketone (MEK) Tetrahydrofuran
Flash Point	-14 °C (6 °F)

Typical Performance Characteristics

Temperature: 22 °C (72 °F)

Attribute Name	Test Method	Value
T-Peel Adhesion	ASTM D1876	10 lb/in width ¹

¹ Metal to Metal Structural Applications

The following typical performance data obtained in the 3M Laboratory under the conditions specified with a cure cycle of 75 psi bonding pressure applied by a platen press and a 60min, 350°F (177°C) cure cycle.

Electrical and Thermal Properties

Attribute Name	Test Condition	Value
Glass Transition Temperature (Tg)	Mid-Point	95 °C (203 °F) ¹
Coefficient of Thermal Expansion	-20°C to 70°C	262 x 10 ⁻⁶ m/m/°C
Coefficient of Thermal Expansion	100°C to 120°C	543 x 10 ⁻⁶ m/m/°C

¹ Glass Transition Temperature (Tg) determined using DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.

Temperature: 22 °C (72 °F)

Attribute Name	Test Method	Test Condition	Value
Dielectric Constant	ASTM D150	1 KHz	5.2
Dissipation Factor	ASTM D150	1 KHz	0.011
Volume Resistivity	ASTM D257		1.2 x 10 ¹⁵ Ω-cm

Handling/Application Information

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user.

The following cleaning methods are suggested for common surfaces:

Steel:

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.

Aluminum:

1. Vapor Degrease: Perchloroethylene condensing vapors for 5-10 minutes.*
2. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
3. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 2°C).
Sodium Dichromate 4.1-4.9 oz./gallon
Sulfuric Acid, 66°Be 38.5-41.5 oz./gallon
2024-T3 aluminum (dissolved) 0.2 oz./gallon minimum
Tap Water Balance of Volume

Note: Review and follow component supplier's environmental health and safety information prior to preparation of this etch solution.

4. Rinse: Rinse panels in clear running tap water.
5. Dry: Air dry 15 minutes; force dry 10 minutes at 150°F ± 5°F (66°C ± 2°C).

Plastics/Rubbers:

1. Wipe with isopropyl alcohol.*
2. Abrade using fine grit abrasives.
3. Wipe with isopropyl alcohol.*

Glass:

1. Solvent wipe surface using acetone or methyl ethyl ketone (MEK).*
2. Apply a thin coating (0.1 mils or less) or primer such as 3M™ Scotch-Weld™ Primer EC-3901 to the glass surfaces to be bonded and allow the primer to dry before bonding.

***Note:** When using solvents, extinguish all ignition sources and follow manufacturer's precautions and directions for use.

Application Techniques

3M™ Scotch-Weld™ Epoxy/Adhesive Coating 2290 can be applied by brushing, flow coating, dip coating, roll coating, knife coating and spraying. For spray application, use a DeVilbiss JGA-70-FX spray gun or equivalent applicator. The atomizing air should be approximately 30 psi. Apply the adhesive at a dry film thickness of 1 mil if coating only one surface. If coating two surfaces, apply a 0.5 mil dry film to each surface. For film thickness less than 1 mil, it may be necessary to dilute Scotch-Weld 2290. For dilution, a 4 parts by weight methyl ethyl ketone to 1 part by weight tetrahydrofuran solution should be made. (A dilution of 1 part of this solution to 1 part of Scotch-Weld 2290 will give a dried film thickness of approximately 0.5 mil). Coverage per 1 mil dry film thickness is approximately 300 sqft/gal.

Cure Cycle

Adhesive B Stage Cycles:

Scotch-Weld 2290 will air dry to a tack free coating in approximately 10-15 minutes @ 75°F (24°C). However, for optimum performance the drying time at 75°F (24°C) should be followed by any of the B stage cycles below:

- Temperature Time
200°F (93°C) 45 minutes
250°F (121°C) 30 minutes

300°F (149°C) 10 minutes

After B-staging, Scotch-Weld 2290 need not be cured immediately. Protect the coated surface from contamination introduced by dust, fingerprints, oil, etc. Wrapping in unplasticized Kraft paper is generally satisfactory. Storage for 2-3 months is permissible.

Cure Cycle

Curing is accomplished with heat. Scotch-Weld 2290 must reach a minimum of 335°F (168°C) for curing to be initiated. A curing temperature of 350°F (177°C) for 30-60 minutes under a pressure of 75 psi is suggested for optimum results. Allow time for the bond lines to reach the cure temperature before timing the cycle. With experimentation and evaluation by the user, lower pressure and/or higher temperature cures for shorter times can be used to make satisfactory bonds depending upon the end use requirements of each individual application.

Storage and Shelf Life

Store products at 60-80°F (15-27°C) for maximum storage life.

3M™ Scotch-Weld™ Epoxy Adhesive/Coating 2290 will have a shelf life of 18 months from date of manufacture in unopened containers. Rotate stock on a “first in-first-out” basis.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for Health and Safety Information before using this product.

Automotive Disclaimer

Select Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M
Industrial Adhesives and Tapes Division
3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-362-3550

3M and Scotch-Weld are trademarks of 3M Company.
©3M 2022 (5/22)