

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT


Client : National Flooring Distributors 58 Blanck Street Ormeau QLD 4208

 Test Number
 :
 23-001101

 Issue Date
 :
 18/04/2023

 Print Date
 :
 18/04/2023

Hybrid flooring planks Colour : Lt brown timber effect End Use : Flooring-Click system Nominal Composition : PVC with infused Polymer Core
End Use : Flooring-Click system
3 9
Nominal Composition : PVC with infused Polymer Core
Nominal Thickness : 8mm



293470

63638

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

hald

Fiona McDonald



Page 1 of 2

AICHAEL A. JACKSON B.Sc.(Hons)



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client :	National Flooring Distributors				
	58 Blanck Street				
	Ormeau QLD 4208				

Test Number	:	23-001101		
Issue Date	:	18/04/2023		
Print Date	:	18/04/2023		

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival	21-03-2023					
Date Tested	18-04-2023					
CHF Value	1	2	3	Mean		
Length	9.3	9.5	9.7	9.5	kW/m²	
Width	9.5	-	-	-	kW/m²	
Smoke Value	1	2	3	Mean		
Length	144	101	142	129	%.min	
Width	174	-	-	-	%.min	
Observations:						
Melting				Yes		
Blistering				Yes		

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

293470

63638

C Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Page 2 of 2

MICHAEL A. JACKSON B.Sc.(Hons)

Fiona McDonald APPROVED SIGNATORY