



*Reduce Your Risk!*<sup>®</sup>

**Independent Slip Testing Services**

GLOBAL PRODUCT CLASSIFICATION

# TEST REPORT

SLIP RESISTANCE CLASSIFICATION OF  
NEW PEDESTRIAN SURFACE MATERIALS

AS 4586-2013

Appendix A - Wet Pendulum Testing

*Prepared For:*

National Flooring Distributors

*Product Description:*

Stella Luxury, Brown, Vinyl Plank 17x30cm

*Issue Date:* 17-01-2022

*Page:* 1 of 6

 +61 (0) 411 600 733

 +64 (0) 279 735 266

[www.gpcsliptesting.com.au](http://www.gpcsliptesting.com.au)



## TEST REPORT- Wet Pendulum Slip Resistance Classification (Australian Standard)

**Report Prepared for:**

National Flooring Distributors  
58 Blanck Street,  
Ormeau QLD 4208

Page #: 2 of 6  
Program #: 8005

**Test Date:**

14-01-2022

**Test Site:**

Independent Slip Testing Services- Slip Resistance Testing Facility (Lota Headquarters QLD Australia)

**Testing Technician:**

J.Kirwood

**Testing Instrument:**

Pendulum Skid Tester with Slider 96 (4S) rubber  
Testing Instrument W1- Serial #: SK1105

### TESTING SPECIMEN DESCRIPTION, SIZE, COLOUR, TYPE, & COATING (if applicable)

1. 1x Stella Luxury, Brown, Vinyl Plank, Sample Size 17x30cm
2. 1x Stella Luxury, Brown, Vinyl Plank, Sample Size 17x30cm
3. 1x Stella Luxury, Brown, Vinyl Plank, Sample Size 17x30cm
4. 1x Stella Luxury, Brown, Vinyl Plank, Sample Size 17x30cm
5. (4 x samples tested in 5 x locations)

**Surface Condition:**

Fine Textured

**Cleaning:**

Tested as received

**Fixed/ Unfixed:**

Unfixed

**Rz Mean:**

n/a

**Environmental Conditions:**

Air conditioning

**Air Temp:**

24 Deg.C

**Direction of Test:**

As indicated on underside of sample

**Slope:**

n/a

### AS 4586-2013

#### INTERPRETATION OF THE WET PENDULUM RESULTS

| Classification | Pendulum mean BPN<br>Slider 96 (4S) rubber |
|----------------|--|
| P5             | >54  |
| P4             | 45-54                                      |
| P3             | 35-44                                      |
| P2             | 25-34                                      |
| P1             | 12-24                                      |
| P0             | <12  |

### TEST RESULTS

|            |        |                             |        |
|------------|--------|-----------------------------|--------|
| #1 Result: | 44 BPN | Slider condition (P400):    | 84 BPN |
| #2 Result: | 41 BPN | Slider condition (Lapping): | 59 BPN |
| #3 Result: | 44 BPN | Temperature adjustment:     | N/A    |
| #4 Result: | 41 BPN | Carpet surface tested dry:  | N/A    |
| #5 Result: | 43 BPN |                             |        |

### CLASSIFICATION

| CLASSIFICATION | PENDULUM MEAN BPN (4S rubber) |
|----------------|-------------------------------|
| <b>P3</b>      | <b>43</b>                     |

The mean results of the five specimens is reported (rounded to nearest whole number)

^ An individual result both below the result classification and below the mean result minus 20% shall be considered of lower classification


|  |       |
|--|-------|
| Maximum Slope Design Value (when dry): | 4 deg |
| Maximum Slope Design Value (when wet): | N/A   |

^NCC Code provides reference for ramps up to 1:8

**DISCLAIMER:**

ISTS accepts no civil liability or responsibility for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report. The test report is intended for viewing purposes solely for the named recipient identified above. The slip test report remains the property of ISTS. This report contains privileged and confidential information. The unauthorised reproduction

Accredited for compliance with ISO/IEC 17025 testing and calibration. NATA is a signatory to the APLAC mutual recognition arrangement for the mutual recognition of the equivalence of testing, calibration and inspection reports.



Signatory: Mick Walton



Testing was carried out using the Wet Pendulum Test Method  
in accordance with Australian Standard AS 4586-2013 Appendix A

## INTERPRETING WET TEST RESULTS

### How to interpret your wet test report...

Wet test results offer six possible outcomes- classification 'P0', 'P1', 'P2', 'P3', 'P4' or 'P5'.

The classification 'P0' reflects a lesser slip resistant surface, while 'P5' classification reflects the greatest slip resistance classification.

There are two parts to this interpretation guide- Firstly the 'National Construction Code requirements', and secondly 'Other Particular Applications' recommendations.

For the 'Global Product Classification' test results refer additional #Note below.

**Step 1.** Note the test location described in the left side column of your report, and the corresponding test result 'P' classification achieved (listed in the far right side column)

**Step 2.** From this interpretation guide, identify the most appropriately related location description described in either 'TABLE 3A' (Part 1) or 'TABLE 3B' (Part 2). Note the 'P' classification listed to the right of this description.

**Step 3.** If the test result classification listed meets (or exceeds) the related 'P' classification from 'TABLE 3A' or 'TABLE 3B', the test surface is meeting the relevant requirement.

**#Note.** For 'Global Product Classification' test reports the 'TABLE 3A' or 'TABLE 3B' descriptions assist in identifying the product's suitability for various applications.

**\*TABLE 2** Classification of Pedestrian Surface Materials according to the AS 4586-2013 wet pendulum test

| CLASSIFICATION | Pendulum* mean BPN          |                          |
|----------------|-----------------------------|--------------------------|
|                | Four S rubber ( Slider 96 ) | TRL rubber ( Slider 55 ) |
| P5             | >54                         | >44                      |
| P4             | 45-54                       | 40-44                    |
| P3             | 35-44                       | 35-39                    |
| P2             | 25-34                       | 20-34                    |
| P1             | 12-24                       | < 20                     |
| P0             | <12                         | -                        |

## TREATMENT OPTIONS

For test results that achieve a result below recommendations, the following treatment options are available to increase slip resistance and Reduce Your Risk!

*While ISTS is solely an audit service, following is a short list of common types of treatments we see our clients using to improve the slip resistance of various pedestrian surface materials.*

|                             |  |
|-----------------------------|--|
| <b>Cleaning procedures</b>  | Minimising detergent residue build up or other contaminants. |
| <b>Acid etching</b>         | Increasing surface texture.                                  |
| <b>Coatings and sealers</b> | Surface coatings and penetrative types.                      |
| <b>Surface texture</b>      | Coatings, etchants, sandblasting, shot blasting, etc.        |
| <b>Surface replacement</b>  | May be the most cost effective option in some instances.     |

*An internet search for 'flooring treatments' will identify surface treatment professionals in your local area. ISTS recommends sourcing a number of detailed proposals when considering treatments, outlining expected slip resistance improvements, visual changes, clean ability and life expectancy.*

## NATIONAL CONSTRUCTION CODE COMPLIANCE CLASSIFICATIONS

Minimum wet pendulum test result classifications to meet National Construction Code requirements.

### \* TABLE 3A

| Location   | Classification |
|--|----------------|
| <b>Stair Treads and Stairway Landings in Buildings</b> - Covered by NCC Volumes 1 - 2            |                |
| 1. Stair treads and a stairway landing (when dry)  | P3             |
| 2. Stair treads and a stairway landing (when wet)  | P4             |
| <b>Nosings for Stair Treads and Landings in Buildings</b> - Covered by NCC Volumes 1 - 2         |                |
| 1. Dry stair tread, a stair non-skid nosing strip and a stairway landing                         | P3             |
| 2. Wet stair tread, a stair non-skid nosing strip and a stairway landing                         | P4             |
| <b>Ramps in Buildings</b> - Covered by NCC Volumes 1 - 2   |                |
| 1. Ramps not steeper than 1:14 (4.1 degrees) gradient (when dry)                                 | P3             |
| 2. Ramps not steeper than 1:14 (4.1 degrees) gradient (when wet)                                 | P4             |
| 3. Ramps steeper than 1:14 (4.1degrees) up to but not steeper than 1:8 (7.1 degrees) (when dry)  | P4             |
| 4. Ramps steeper than 1:14 (4.1 degrees) up to but not steeper than 1:8 (7.1 degrees) (when wet) | P5             |

## ADDITIONAL NOTES & REFERENCES

### References

\*Table 3A- HB198:2014 "Guide to the specification and testing of slip resistance of pedestrian surfaces" Standards Australia Limited 2014.

\*Table 2- AS 4586-2013 "Slip resistance classification of new pedestrian surface materials".

*nb. The information provided is intended as a guide only, consult the referenced publications for further information in regards to measurement results and recommendations.*

**\* TABLE 3B** Minimum wet pendulum test result classifications for other applications where the NCC does not apply.

| Location   | Classification  |
|--|---|
| <b>External Pavements and Ramps</b>  |   |
| 1. External ramps including sloping driveways, footpaths etc. steeper than 1 in 14 (4.1°)  | P5  |
| 2. External ramps including sloping driveways, footpaths, etc., under 1:14 (4.1°), external sales areas (eg. markets), external car park areas, external colonnades, walkways, pedestrian crossings, balconies, verandas, carports, driveways, courtyards and roof decks | P4  |
| 3. Undercover car parks  | P3  |
| <b>Hotels, Offices, Public Buildings, Schools and Kindergartens</b>  |   |
| 1. Entries and access areas including...<br>hotels, offices, public buildings, schools, kindergartens,<br>internal lift lobbies and common areas of public buildings   | Wet area P3<br>Transitional area P2<br>Dry area P1 (see Note 3) |
| 2. Toilet facilities in offices, hotels and shopping centres   | P3  |
| 3. Hotel apartment bathrooms, ensuites and toilets   | P2  |
| 4. Hotel apartment kitchens and laundries  | P2  |
| <b>Loading Docks, Commercial Kitchens, Cold Stores, Serving Areas</b>  |   |
| 1. Loading docks under cover and commercial kitchens   | P5  |
| 2. Serving areas behind bars in public hotels and clubs, cold stores and freezers  | P4  |
| <b>Supermarkets and Shopping Centres</b>   |   |
| 1. Fast food outlets, buffet food servery areas, food courts and fast food dining areas in shopping centres  | P3  |
| 2. Shop and supermarket fresh fruit and vegetables area  | P3  |
| 3. Shop entry areas with external entrances  | P3  |
| 4. Supermarket aisles (except fresh food areas)  | P1 (see Note 3)   |
| 5. Other separate shops inside shopping centres - wet  | P3  |
| 6. Other separate shops inside shopping centres - dry  | P1 (see Note 3)   |
| <b>Swimming Pools and Sporting Facilities</b>  |   |
| 1. Swimming pool ramps and stairs leading to water   | P5  |
| 2. Swimming pool surrounds and communal shower rooms   | P4  |
| 3. Communal changing rooms   | P3  |
| 4. Undercover concourse areas of sports stadiums   | P3  |
| <b>Hospitals and Aged Care Facilities</b>  |   |
| 1. Bathrooms and ensuites in hospitals and aged care facilities  | P3  |
| 2. Wards and corridors in hospital and aged care facilities  | P2  |

**\*TABLE 2** Classification of Pedestrian Surface Materials according to the AS 4586-2013 wet pendulum test

| Classification | Pendulum* mean BPN          |                          |
|----------------|-----------------------------|--------------------------|
|                | Four S rubber ( Slider 96 ) | TRL rubber ( Slider 55 ) |
| <b>P5</b>      | <b>&gt;54</b>               | <b>&gt;44</b>            |
| <b>P4</b>      | <b>45-54</b>                | <b>40-44</b>             |
| <b>P3</b>      | <b>35-44</b>                | <b>35-39</b>             |
| <b>P2</b>      | <b>25-34</b>                | <b>20-34</b>             |
| <b>P1</b>      | <b>12-24</b>                | <b>&lt; 20</b>           |
| <b>P0</b>      | <b>&lt;12</b>               | <b>-</b>                 |

**P1 (see Note 3)**

**Note 3.**

The minimum classification listed in Table 3B is P1. It is inappropriate for Table 3B to list the lower classification, P0, since there is no lower limit on Classification P0.

Notwithstanding, some smooth and polished floor surfaces, which do not achieve Classification P1, may be considered to provide a safe walking environment for normal pedestrians walking at a moderate pace, provided the surface is kept clean and dry; however, should these surfaces become contaminated by either wet or dry materials, or be used by pedestrians in any other manner, then they may become unsafe. Therefore, the type of maintenance, the in-service inspection of floors, other environmental conditions and use should be taken into account when selecting such products.

**ADDITIONAL NOTES & REFERENCES**

**References**

\*Table 3B- HB198:2014 "Guide to the specification and testing of slip resistance of pedestrian surfaces" Standards Australia Limited 2014.

\*Table 2- AS 4586-2013 "Slip resistance classification of new pedestrian surface materials".

*nb. The information provided is intended as a guide only, consult the referenced publications for further information in regards to measurement results and recommendations.*

## TEST PRODUCT IMAGE

**Product Description:** Stella Luxury, Brown, Vinyl Plank  
17x30cm

**Test Date:** 14-01-2022



## END OF TEST REPORT

*Have a successful day!*

***...Considering pedestrian surface enhancements,  
or developing your property?***



地板产品的抗滑性测量

If you are selecting, purchasing or installing pedestrian surface materials, an independent, accredited classification is a useful tool providing confidence to all stakeholders the product will perform as specified.

Independent Slip Testing Services is the global leader in accredited slip resistance measurement and classification of pedestrian surface materials prior to installation.

see the ISTS 'GPC Results Interpretation Booklet' for guidance on pedestrian surface product selection.

**TILES PAVERS STONE TIMBER VINYL RUBBER METAL TAPES COATINGS GRATINGS CONCRETE  
CARPETS STEP-NOSINGS TACTILES MOSAICS GLASS**

Contact us any time if you have questions.  
Have a successful day!



Slip Testing

Recommended Slip Classifications  
National & Global Guides  
Slope Conversions



www.gpcsliptesting.com

