



Description

Kemiko Stone Tone Sealer II is a low viscosity, low odor, single component, water base acrylic sealer that can be used to protect bare concrete, Kemiko Stone Tone Stain acid stained concrete and Kemiko Rembrandt polymer stained concrete, without giving a wet look. This user-friendly, easy-to-apply coating is designed to be a waterproofing sealer for horizontal and vertical cementitious substrates such as concrete and masonry. Benefits include low VOC, chemical resistance, stain resistance and UV resistance. Kemiko Stone Tone Sealer II is available in a clear high gloss finish and is an excellent replacement product for high VOC lacquers, acrylics and varnishes.

Applications

Kemiko Stone Tone Sealer II can be applied over properly prepared concrete, Kemiko Stone Tone stains, and Kemiko Rembrandt polymer stains as a resilient protective finish coat. Typical applications include: commercial and residential concrete floors, hospitals, showroom floors, schools, shopping malls, patios, walkways and many other interior or exterior floor surfaces that require additional protection.

Physical Characteristics

Kit Size	1 gallon and 5 gallon kits available
Colors Available	Clear High Gloss Finish
Volume Solids	<25% Volume Solids
VOC Contents	<100g/L (Theoretical), Compliant to SCAQMD Rule 1113
Specific Gravity	1.01 (Theoretical)
Gloss	@60°, >90 Gloss Units, (ASTM D523)
Hardness	F (ASTM D3363)
Adhesion	Tape Test Result: 3B (ASTM 3359)
Film Thickness	3-4 mils (0.076-0.10mm) wet film thickness
Coverage per Kit	1 gallon: 300ft ² -500ft ² (27.9m ² -46.5m ²) at recommended film thickness 5 gallon: 2000ft ² -2500ft ² (185.8m ² -232.3m ²) at recommended film thickness <i>Note: Coverage rates will vary depending on surface texture and porosity.</i>
Dry/Recoat Time	Dry to Touch: 2-3 hours Light Foot Traffic: 8-10 hours Heavy Traffic: 20-24 hours Full Chemical and Physical Resistance Cure: 3-5 days Recoat Window: Within 3 hours after product reaches Dry to Touch state <i>Note: Product tested at 77°F (25°C), 50%RH. Dry and recoat times will depend on temperature, humidity and other conditions relative to the environment.</i>
Odor	Low
Primers	None required
Thinning	Do not thin
Clean Up	Warm water and mild soap
Shelf Life	12 months from date of manufacture



**Concrete
Coatings &
Floor Systems**

TECHNICAL BULLETIN

Kemiko® Stone Tone Sealer II Gloss (46C-1)

Packaging Description

Weight per Kit:

1Gal: 8.44lbs (3.83kg) 5Gal: 42.20lbs (19.14kg)

Kemiko Stone Tone Sealer contains:

8.44lbs (3.83kg) / 1Gal (3.78L) of product in a premeasured 1 gallon (3.78L) container
42.20lbs (19.14kg) / 5Gal (18.93L) of product in a premeasured 5 gallon (18.93L) container

Environmental Conditions

Apply between 50°F-80°F (10°C-27°C) and 5°F above dew point. Avoid using in direct sunlight. Do not apply on rainy or foggy days.

Storage Conditions

Store between 50°F-100°F (10°C-32°C). Keep in a cool, well-ventilated area, away from direct sunlight and heat. Store in a segregated and safe area, avoiding all possible sources of ignition.

Safety

Care should be taken when using this product. During application, use proper protective equipment including, but not limited to: protective eyewear, proper respirator and protective gloves. Ensure work spaces are well-ventilated. Refer to the Application Bulletin for application information. Refer to product label and SDS carefully for more detailed safety information prior to use or handling.

Disclaimer

Information provided in this Technical Bulletin is based on laboratory testing and is used as a guideline only. Customer should test the material for their specific application and under their application conditions before using the product on a project.

Warranty

The following warranty is made in lieu of all other warranties, either expressed or implied. This product is manufactured of selected raw materials by skilled technicians. Neither seller nor manufacturer has any knowledge or control concerning the purchaser's use of this product and no warranty is made as to the results of any use. The only obligation of either seller or manufacturer shall be to replace any quantity of this product, which is proved to be defective. Any claim of defective product must be received in writing within one (1) year from date of shipment. Neither seller nor manufacturer assumes any liability for injury, loss or damage resulting from use of this product.

Contact EPMAR for any additional application information



Epmar Corporation
13240 Barton Circle, Whittier, CA 90605-3254
Ph: 562.946.8781 / Fax: 562.944.9958
www.epmar.com / www.kemiko.com