

TECHNICAL DATA SHEET

LevelSlope

PRODUCT AND COMPANY IDENTIFICATION	
PRODUCT MANUFACTURER: Stone Edge Surfaces	MANUFACTURER: Turley International Resources, LLC.
product name: LevelSlope	4322 South 80 th Street
	Mesa, AZ 85212 - USA
	TEL: 844-786-6333 E: info@stoneedgesurfaces.com
EMERGENCY: Call 911 or seek medical assistance immediately	MEDICAL: Call 911 or seek medical assistance immediately

PRODUCT COMPOSITION

Stone Edge Surfaces LevelSlope is ASTM E84 Fire and Smoke Class A Certified, and is a Multi-Use, Non-Hydrophobic, Pre Sanded, Fiber Reinforced Commercial Grade, Just-Add-Water, No Primer Required, Heavily Polymerized Extreme Bonding Concrete mix that has high flexural strength, extreme adhesion qualities, and is easily troweled or pumped. LevelSlope can be used as an Extreme Bonding Base Coat, an Underlayment and Repair Concrete, as well as having a high enough PSI to be a wearable Top Coat surface where it can be troweled smooth or a broom finish applied. Just like our standard LevelSlope, LevelSlope can be used to patch and repair spalled and damaged concrete areas, but unlike LevelSlope, LevelSlope can also be a standalone wearable Top Coat. LevelSlope is also used for deep fill applications from thin up to 4 inches deep. LevelSlope creates an incredibly strong and durable physical and chemical bond with a substrate and can be placed over concrete, stucco, plaster, drywall, Styrofoam, brick, block, tile, some wood, rLevelSlope

oof deck material, and much more. LevelSlope is durable, water resistant, and does not expand, contract, or warp when exposed to moisture.

MIXING & USE INSTRUCTIONS

MIXING INSTRUCTIONS: NOTE: LevelSlope is a "just add water" dry polymeric concrete mix. When mixing, add water to container first then add dry mix. Use cool, clean potable water and in hot climates you can ice your water. **SLOPING - BASE COAT – UNDERLAYMENT - CONCRETE REPAIR - DEEP FILL:** Use 2.75 – 3.75 QUARTS (2.60 - 3.54 L) WATER per 50# (22.68kg) bag. Start at 2.75 Quarts of water and add more water as needed. **PUMPING:** Recommend a 30+ GPM Max Discharge rate pump with capacity of 8 to 10 - 50# bag batch minimum (Strong Super80 or Placer type). Use 4 – 4.5 QUARTS (3.78 – 4.25 L) WATER per 50# (22.68kg) bag (start with 4 Quarts and add more water as needed). **NOTE: More/Less water** may be required depending on air temp., humidity, and water mineral content as water chemistry varies by location. **MIXING:** Mix for 3 minutes with mechanical mixer after all dry material has been added to water, add more water, if necessary, not to exceed maximum amounts listed above without testing workability and dry time. **APPLICATION:** For Pumping (see pumping instructions above). For Troweling, you can trowel tight over Lath, use a gauge Rake, Smoother, squeegee, or a magic trowel. **DRY and SET TIME:** Varies by thickness from 1 to 24 hours.

PRODUCT USES

Most Common Use & Finishes (Not a Complete List) Base Coat. Underlayment. Create positive slope. Concrete Patch and Repair. Can be used on Exterior Walls, Block and Retaining Walls, Home Facades, Waterfalls, Fireplaces, Outdoor Kitchens, Pillars, Shower Walls, and Commercial Building Facades. It can also be used as a high traffic area refurbishment coating, Light and Deep Fill, and as a wearable top coat smooth or broom finish. LevelSlope can also be colored and can take stains, topical or integral colors.

I					C	Coverag	ge			
	Thickness	1/8" Thick	3/16" Thick	1/4" Thick	3/8" Thick	1/2" Thick	3/4" Thick	1" Thick	1.5" Thick	2" Thick
	SQFT Covered Per Bag	48	36	24	16	12	8	6	4	3

Coverage will vary depending on porosity and condition of substrate as well as human factor of technique of application and tools used to obtain desired depth. See full product coverage below

PRODUCT CAUTIONS

Product must be installed over a stable substrate using proper preparation and installation procedures. All loose materials, or materials that are likely to come loose, must be removed from substrate before product is applied to reduce the risk of delamination. All expansion/cut joints in the existing substrate must be honored. Extra joints may be added as deemed necessary by the installer. Recommended temperature of air and surface for LevelSlope application is 40-95F (4.4 to 35C). Ideal temperature for application is 70F (21.11C). Make sure surface area is cool before applying. If forecast or substrate temperature is below 40F (4.4C) at the time of application DO NOT proceed with application. LevelSlope is highly adhesive and will adhere to just about everything so make sure to clean any excess LevelSlope off tools, work area surroundings, etc., before it fully cures.

PRODUCT PHYSICAL PROPERTIES

ITEM	TESTING USED or MEETS OR EXCEEDS	RESULTS or MEETS OR EXCEEDS
Compressive Strength:	ASTM C 39	5,100 psi
Flexural Strength:	ASTM C 78	1,210 psi
Adhesion:	MIL-D-3134 Para. 3.7.14 (Shear from steel plate after 96 hours)	312 psi
Water Absorption:	ASTM C624	4.2%
Tensile Strength:	ASTM C190	655 psi
Resistance to Elevated Temperatures:	MIL-D-3134, Para. 4.7.5.1	No Flow or Slip
Abrasion Resistance:	ASTM C 779	.13 in" (300 cycles)
Coefficient of Thermal Expansion:	ASTM C531	6.8 E-04
Electrical Conductivity:		Dielectric
Flammability - Flame Spread Index:	ASTM E84-19b Flame Spread Index	FSI: 0 (Certified CLASS A)
Smoke Development Index:	ASTM E84-19b Smoke Development Index	SDI: 10 (Certified CLASS A)
Freeze Thaw:	ASTM C 666/C 666M-03 (Standard Test Method for Resistance of Concrete to Freezing and Thawing, Procedure A - Freezing and Thawing in Water) The relative dynamic modulus indicates that Product is:	Freeze-thaw durable after 300 cycles.



TECHNICAL DATA SHEET

LevelSlope

RODUCT B	CINEFI	3									
One Compone	nt Mix. N	o Liquic	l Polym	iers to	add. Ju	ust add	l water	on Job	o site.		No VOC (volatile organic compound) emission
Reinforced wit	n Latest,	State o	f The A	rt Poly	mers a	and Fib	ers.				Contributes to USGBC credits under LEED rating system.
Polymers used standing wate		n-hydro	phobic	″ & wi	ill not v	weaker	n or re	-emuls	ify in		Abrasion and wear resistant
Application Fle	kibility: F	ump, S	creed R	Rake, T	rowel,	Magic	Trowe	el, Sque	egee		Extremely Self Adhesive
Warranted bo	dability										Can be used vertically, horizontally or overhead
Moisture toler	int and b	reathal	ble								Water clean up
Extremely Adh	esive as a	a Morta	r Bed o	or Thin	Set fo	r Tile					Can be applied thin or deep fill
Can be mixed	hicker fo	r Slopin	Ig								
RODUCT	FANA	BILIT	Y								
As a Top Coat, in and stain c corresponding resistant prop	once dry increte, skid resi rties. As	it will s stance, a preca	oak in and th	and s e mor	tain Le e diffic	evelSlo cult to	pe. In clean.	gener The sr	al, the noothe	mor er the	e aggressive the finished surface the greater the coefficient of friction ar finished texture the easier the surface is to clean, but there is a loss of sk
As a Top Coat, in and stain c corresponding	once dry increte, skid resi rties. As ea befor	it will s stance, a preca e use.	oak in and th	and s e mor	tain Le e diffic	evelSlo cult to	pe. In clean.	gener The sr	al, the noothe	mor er the	e aggressive the finished surface the greater the coefficient of friction an finished texture the easier the surface is to clean, but there is a loss of ski
As a Top Coat, in and stain c corresponding resistant prop conspicuous a RODUCT C	once dry oncrete, skid resi rties. As ea befor OVER/	it will s stance, a preca e use. AGE	and th utionar	and s ie mor ry step	tain Le e diffic , Stone	evelSlo cult to e Edge S	pe. In clean. Surface	gener The sr es recc	al, the noothe mmen	more er the ids th	e aggressive the finished surface the greater the coefficient of friction an finished texture the easier the surface is to clean, but there is a loss of ski
As a Top Coat, in and stain c corresponding resistant prop conspicuous a RODUCT C	once dry oncrete, skid resi rties. As ea befor OVER vary dep	it will s stance, a preca e use. AGE ending	on con	and s ie mor ry step ditions	stain Le le diffic o, Stone 5, amou	evelSlo cult to e Edge : unt and	pe. In clean. Surface	gener The sr es reco of wate	al, the noothe mmen	more er the ids th	
As a Top Coat, in and stain c corresponding resistant propi conspicuous a RODUCT C Coverage may results may va Thickness 1/32	once dry oncrete, skid resi rties. As ea befor OVER/ vary dep y. Avera	it will s stance, a preca e use. AGE ending ge cove	on con- a/16"	and s ie mor ry step ditions er 50 L	stain Le re diffic o, Stone s, amou b bag: 3/8"	evelSlo cult to e Edge s unt and Appros	pe. In clean. Surface d type ximate 3/4"	gener The sr es reco of wate	al, the noothe mmen er used qft ove	more er the ids the d, app er 2.5	e aggressive the finished surface the greater the coefficient of friction an finished texture the easier the surface is to clean, but there is a loss of sk at the end-user test their cleaning and disinfecting compounds on a small nor plication methods, skill level, and overall thickness of your application, your metal lath.
As a Top Coat, in and stain c corresponding resistant prop conspicuous a RODUCT C Coverage may results may va	once dry oncrete, skid resi rties. As ea befor OVERA vary dep y. Avera	it will s stance, a preca e use. AGE ending ge cove	on con	and s e mor ry step ditions er 50 L	stain Le re diffic o, Stone s, amou b bag:	evelSlo cult to e Edge : unt and Appro:	pe. In clean. Surface d type	gener The sr es reco of wate	al, the noothe mmen er used qft ove	more er the ids th	e aggressive the finished surface the greater the coefficient of friction ar finished texture the easier the surface is to clean, but there is a loss of sk at the end-user test their cleaning and disinfecting compounds on a small no plication methods, skill level, and overall thickness of your application, your metal lath.
As a Top Coat, in and stain c corresponding resistant prop- conspicuous a RODUCT C Coverage may va Thickness 1/32 Thickness 1/32 Coverage 1880	once dry oncrete, skid resi rties. As ea befor DVER/ vary dep y. Avera 1/16" Thick 90	it will s stance, a preca e use. AGE ending ge cove 1/8" Thick 48	on con 3/16" Thick	and s le mor ry step ditions er 50 L 1/4" Thick	tain Le e diffic , Stone 5, amou b bag: 3/8" Thick	evelSlo cult to e Edge s unt and Appro:	pe. In clean. Surface d type ximate 3/4" Thick	gener The sr es reco of wate	al, the noothe mmen er used qft ove	more er the ids the d, app er 2.5	e aggressive the finished surface the greater the coefficient of friction ar finished texture the easier the surface is to clean, but there is a loss of sk at the end-user test their cleaning and disinfecting compounds on a small no plication methods, skill level, and overall thickness of your application, your metal lath.
As a Top Coat, in and stain c corresponding resistant prop conspicuous a RODUCT C Coverage may results may va Thickness 1/32 Thickness 1/32	skid resi rties. As ea befor OVERA vary dep y. Avera 1/45" Thick 90 HELF L	it will s stance, a preca e use. AGE ending ge cove 1/8" Thick 48	on con- rage pe ^{3/16"} 3/16	and s and and and s and	tain Le e diffic o, Stone b bag: <u>3/8"</u> <u>Thick</u> 16	evelSlo cult to e Edge s unt and Appro: 1/2" Thick 12	pe. In clean. Surface d type (ximate 3/4" Thick 8	gener The sr es reco of wate	al, the noothe mmen er used qft ove 1.5" Thick 4	more er the ids thi d, app er 2.5 2" Thick 3	e aggressive the finished surface the greater the coefficient of friction an finished texture the easier the surface is to clean, but there is a loss of sk at the end-user test their cleaning and disinfecting compounds on a small nor plication methods, skill level, and overall thickness of your application, your metal lath.