

A Reliable Power Solution Provider

Lithium Iron Phosphate (LiFePO4) Battery

TN-LFP12.8V24AH


Features

- Using the technology of lithium iron phosphate cell, superior safety, thousands of cycles, 100%DOD, under normal conditions
- Built-in automatic protection for over-charge, over discharge, over current and over temperature
- Maintenance free
- Internal cell balancing
- ♦ Lighter weight: About 40% ~50% of the weight of a comparable lead acid battery.
- Can be charged using most standard lead-acid charges (set)
- ◆ Wider temperature range:-20 ℃~60 ℃

Application

- ♦ UPS
- Solar &Wind power system
- ♦ Golf Cart
- Electric vehicle, E-bike, E-rickshaw e.g.
- ◆ Lighting






General Specifications Nominal Voltage 12.8V **Nominal Capacity** 24Ah@0.2C 307.2Wh Energy Electrical Internal Resistance 60≤mΩ Characteristics Cycle Life >2000 Cycles @ 0.2C Charge/Discharge at 100%DOD,End of Life 70% Capacity. Months Self Discharge ≤3.5% per month at 25℃ 14.6±0.2V Charge Voltage At 0℃~45℃ temperature, charged to 14.6V at a constant current of 0.2C5A, and Charge Mode (CC/CV) then, changed continuously with constant voltage of 14.6V until the current was not Standard Charge more than 0.02C5A 4.8A **Charger Current** 12A Max.Charge Current 4 8A Discharge Current Max. Continuous Current 24A Standard Discharge Max.Pulse Current 60A(<3S) Disxcharge Cut-off Voltage 10.0V Charge Temperature 0° to 45° (32° to 113°) @60±25% Relative Humidity Disxcharge Temperature -20℃ to 60℃(-4೯ to 140೯) @60±25% Relative Humidity Environmental 0℃ to 45℃(32೯ to 113೯) @60±25% Relative Humidity Storage Temperature Water Dust Resistance IP55 Cell & Method IFR32700 N60,4S4P Plastic Case ABS Dimension(L*W*H*TH) 181*77*167*167mm Mechanical Weight 2.9Kg Approx. Terminal M5

Tianneng Battery Group Co.,Ltd


18 Baoqiao Road, Huaxi Industrial Function Zone, Zhejiang, China 313100

Lithium Iron Phosphate (LiFePO4) Battery


TN-LFP12.8V24AH




Different Temperature Discharge Curve @0.5C, 25℃




Different DOD Discharge Cycle Life Curve@0.5C, 25




Charge Characteristics @0.2C&0.5C, 25℃



Charge Characteristics @0.2C&0.5C, 25∾



Open circuit voltage VS SOC%



Tianneng Battery Group Co.,Ltd