



AUTOMOTIVE UNIVERSAL TOUCH-UP AEROSOLS

DESCRIPTION AND USES

Rust-Oleum® Automotive Universal Touch-Up Aerosol is a paint and primer in one that repairs and seals surface scratches. Its weather and UV resistant formula dries fast and provides long lasting protective barrier that seals out moisture and prevents rust and corrosion. It is suitable for use on metal, fiberglass, aluminum and plastic. It is great for use on cars, trucks, vans and SUVs.

Universal Touch-Up Aerosols feature an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

SKU (11 ounce spray)	Description
292320	Universal Gloss Black
292325	Universal Bright White
292326	Universal Silver

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is above 50°F (10°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Rust-Oleum Universal Bonding Primer (286793) is recommended to enhance adhesion and hiding, and is especially recommended for heavily rusted or pitted surfaces.

SURFACE PREPARATION

Clean the area to be painted with mineral spirits to remove all oil, grease, wax and dirt. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. For best results, dry or wet sand with 400-grit sandpaper to feather adjacent paint surfaces and prepare metal.

PRODUCT APPLICATION (cont.)

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 12-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 2 or more light coats a few minutes apart. Apply multiple light coats versus one heavy coat. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes and to handle in 1-2 hours. The surface can be recoated within 2 hours or after 48 hours. If recoating after 48 hours, repeat the preparation steps.

FINISHING

Apply a Rust-Oleum automotive clearcoat for a durable finish. May be buffed with wax or polish after one week.

CLEAN-UP

When finished spraying, clear the spray valve by turning upside down and pushing the spray button for 5 seconds. Clean up wet or dry paint with xylol. Mineral spirits can also be used to remove wet paint. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**TECHNICAL DATA****AUTOMOTIVE UNIVERSAL TOUCH-UP AEROSOLS****PHYSICAL PROPERTIES**

		AUTOMOTIVE UNIVERSAL TOUCH-UP AEROSOLS
Resin Type		Modified Acrylic
Pigment Type		Varies with Color
Solvents		Acetone, Acetates, and Aromatic Hydrocarbons
MIR		0.95 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) per Coat		1.5-2.5 mils (37.5-62.5 μ)
Practical Coverage at Recommended DFT		14-16 sq.ft./can (1.3-1.5 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Recoat	Within 2 hours or after 48 hours
	Fully Dry	48 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		3 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.