



METALLIC BRIGHT REFLECTIVE FINISH

DESCRIPTION AND USES

Rust-Oleum® Metallic Bright Reflective Finish is designed to produce a bright, shiny and distinctive finish. This metallic paint is recommended for interior automotive accessories and including helmets, bikes, and more. The Bright Reflective finish features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

Metallic Bright Reflective Finish is not rub-resistant. It is also not resistant to outdoor conditions. For interior use only.

PRODUCTS

| SKU | Description |
|--------|-------------------|
| 248652 | Metallic Chrome |
| 248653 | Metallic Gold |
| 248655 | Metallic Aluminum |

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Apply when temperature is between 50° and 90°F (10°-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, and wax with Rust-Oleum Wax & Tar Remover. Clean the surface with soap and water or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

PRIMING

Use of a Rust-Oleum Primer provides added corrosion protection on metal and promotes adhesion and hiding. A primer is especially recommended for metal and plastic surfaces. Recommended primers include 249321 Primer Sealer and any of the sandable primers (249419 Red, 252472 Light Gray, or 249415 Gray).

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 10 minutes and is fully dry in 30 minutes. Apply a second coat if necessary at any time. Do not apply a clear topcoat.

CLEAN-UP

Wipe off tip when finished. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



TECHNICAL DATA

METALLIC BRIGHT REFLECTIVE FINISH

PHYSICAL PROPERTIES

| Physical Properties | METALLIC BRIGHT REFLECTIVE FINISH | |
|---|--|------------|
| Resin Type | Hydrocarbon Resin | |
| Pigment Type | Metallic | |
| MIR | 1.25 Max | |
| Fill Weight | 11 ounces | |
| Solvents | n-Butane, Naphtha, Toluene, Xylene | |
| Recommended Dry Film Thickness (DFT) Per Coat | 1.0-2.0 mils (25-50 μ) | |
| Practical Coverage at Recommended DFT (assumes 15% material loss) | 8-10 sq.ft./can (0.7-0.9 m ² /can) | |
| Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity | Touch | 10 minutes |
| | Recoat | Anytime |
| | Fully Dry | 30 minutes |
| Shelf Life | 5 years | |
| Flash Point | -141°F (-96°C) | |
| Safety Information | For additional Information, see SDS | |

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.