



TEXTURED METALLIC

DESCRIPTION AND USES

Rust-Oleum® Textured Metallic is designed to provide a fast-drying, durable coating for customizing trunks, dashboards, tool boxes, and more. Textured Metallic is suitable for use on properly prepared automotive plastics, bare metal, aluminum, fiberglass, primed surfaces or OEM painted surfaces. Textured Metallic features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

SKU (11 ounce spray)	Description
248665	Graphite

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Plastic Surfaces – Thoroughly wipe down the surface with paint thinner to promote proper adhesion. Use of 249 323 Plastic Primer provides excellent adhesion. For aged or weathered surfaces, remove loose material with a dry brush, clean with soap and water, rinse and let dry. If mildew is present, wash with a solution of bleach and water, rinse and let dry.

Metal Surfaces - Wash the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces. Use of 7780830 Clean Metal Primer provides added corrosion protection, enhances adhesion and hiding, and is especially recommended for metal and wood surfaces.

PRODUCT APPLICATION (cont.)

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can 10-12" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface and in motion while spraying. Apply 2 or more light coats a few minutes apart. Maximum paint adhesion and durability is achieved in 5-7 days. Do not use near open flame.

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20-30 minutes, to handle in 1 hour and is fully dry in 24 hours. Apply a second coat or topcoat within 1 hour or after 48 hours.

CLEAN-UP

Wipe off tip when finished. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

**TECHNICAL DATA****TEXTURED METALLIC****PHYSICAL PROPERTIES**

		TEXTURED METALLIC
Resin Type		Modified Alkyd
Pigment Type		Carbon Black and Aluminum Paste
Solvents		Acetone and Aromatic Hydrocarbons
MIR		1.25 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50 μ)
Practical Coverage at Recommended DFT		10-12 sq.ft./can (0.90-1.09 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	20-30 minutes
	Recoat	Within 1 hour or after 48 hours
	Fully Dry	24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.