



INSTRUCTIONS FOR MAKING ONE GALLON OF SLIME/GOOP

1. Measure powdered methyl cellulose based on desired viscosity:
 - Thin viscosity “slime” 1 scoop = 45g powdered methyl cellulose
 - Medium viscosity “goop” 1.5 scoops = 68 g powdered methyl cellulose
 - Heavy viscosity “double thick goop” 2 scoops = 90 g powdered methyl cellulose
2. Divide methyl cellulose powder into two equal parts and set aside.
3. Heat three (3) quarts of water to near boiling and transfer into a one (1) gallon container (or larger).
4. Add one-half of the methyl cellulose powder to the water and stir vigorously until dissolved.
5. Add the other half of the methyl cellulose powder and stir vigorously until dissolved.
6. Add one (1) quart of room temperature or chilled water and stir well. Product will thicken as it cools.