



**CLIENT:** ADAM'S POLISHES, INC.  
8225 North Valley Highway  
Thornton, CO 80221  
United States

Attn: Christopher Gallahar

**Test Report No: 4796814PP01R1**

**Date: 21 July 2021**

*Report supersedes report #4796814PP01 for correction to dating and sample designation.*

**SAMPLE(S) SUBMITTED**

**BY THE CLIENT AS:** 1 – 4" x 8" x 0.25" clear, colorless, glass pane coated with "Graphene Ceramic Advanced".

**DATE OF RECEIPT:** 14 July 2021

**TEST PERIOD:** 20 July 2021

**TEST(S) REQUESTED:** The submitted materials were tested for Pencil Hardness as per ASTM D-3363.

**TEST RESULTS:** See Page 2.

**PREPARED BY:**

**SIGNED FOR AND ON BEHALF OF  
SGS NORTH AMERICA INC.,**

**Kyle Buttigieg, Test Engineer  
Packaging & Materials Lab**

**Frank Savino, Lab Manager  
Packaging & Materials Lab**

**PAGE 1 OF 2**

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/terms-and-conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

SGS North America Inc. | Consumer and Retail Services 291 Fairfield Avenue, Fairfield, NJ 07004 t (973) 575-5252 f (973) 575-

Member of the SGS Group (Société Générale de Surveillance)

CLIENT : ADAM'S POLISHES, INC.

REPORT No: 4796814PP01R1

**TEST RESULT:**

Test :

**Pencil Hardness**  
ASTM D-3363

Specimen	Scratch Hardness
Graphene Ceramic Advanced	No Scratch Observed, 10H

**Notes:** Shorter length of lead than 5 to 6 mm utilized as sample was too smooth for chosen hardness level of test.


Sample tested utilizing 10H pencil provided by client.

Lab conditions: 73° F & 50%RH

Sample Photos



10H Pencil Provided by client



Graphene Ceramic Advanced

\*\*\*\*\*END OF REPORT\*\*\*\*\*