

CLIENT: **ADAM'S POLISHES INC**

8225 North Valley Highway

Thornton CO 80221 **United States**

Attn: Christopher Gallahar

> Test Report No: 4673105PP01 Date: 16 September 2020

SAMPLE(S) SUBMITTED

BY THE CLIENT AS: 1 – 4" x 8" x 0.25" Clear, Colorless, Glass Pane Coated with "Graphene Ceramic

Coating"

14 September 2020 DATE OF RECEIPT:

TEST PERIOD: 16 September 2020

The submitted material was tested for Pencil Hardness as per ASTM D-3363 TEST(S) REQUESTED:

with Client Instruction.

TEST RESULTS: See Page 2

SIGNED FOR AND ON BEHALF OF PREPARED BY:

SGS NORTH AMERICA INC.,

Feal Laure

Hayford Mensah, Report Writer

Frank Savino, Lab Manager **Packaging & Materials Lab Packaging & Materials Lab**

PAGE 1 OF 2

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/terms-and-conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents $at \underline{\ \ } \underline{\ \ }$ jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



CLIENT: ADAM'S POLISHES INC REPORT NO: 4673105PP01

TEST RESULT:

Test: Pencil Hardness


ASTM D-3363

Specimen	Scratch Hardness
Graphene Ceramic Coating	No Scratch Observed, 10H

Note: Scratch Hardness evaluated utilizing supplied 10H pencil.

Lab conditions: 73°F & 50%RH

Sample Photo



*******END OF REPORT******

Page 2 of 2

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sqs.com/en/terms-and-conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sqs.com/en/Terms-and-Conditions/terms-e-document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.