

PAINT PROTECTION FILM

Matte



Performance Properties

Thickness

without liner or cap sheet

7-8 mil

Rock Chip Resistance

Water-worn road gravel, 9.5 mm to 16 mm mesh
(SAE J400 Gravelometer, ASTM D3170-12)

Pass

Chemical Resistance

Isopropyl Alcohol & Heptane/Hexane/MEK
(ASTM D7244, ASTM D6279)

No Detrimental
Effect

Weathering

QUV & Xenon, up to 2500 hrs
(ASTM G153 & ASTM G155)

No Detrimental
Effect

Staining

Transmission Fluid, Antifreeze, Windshield Washing
Fluid & Used Motor Oil, Ketchup, Mustard
(ASTM E313-98)

Resilient

Acid Immersion

10% Sulfuric Acid, 72 hrs

No Detrimental
Effect

Base Immersion

10% Sodium Hydroxide, 72 hrs

No Detrimental
Effect

* Certain restrictions apply; see a dealer for details.

©2020 Eastman Performance Films, LLC. All rights reserved. No liability is accepted for errors. 01/20

