

PAINT PROTECTION FILM

Platinum Extra



Performance Properties

Thickness without liner or cap sheet	10.6-11.6 mil
Rock Chip Resistance Water-worn road gravel, 9.5 mm to 16 mm mesh (SAE J400 Gravelometer, ASTM D3170-12)	Pass
Chemical Resistance Isopropyl Alcohol & Heptane/Hexane/MEK (ASTM D7244, ASTM D6279)	No Detrimental Effect
Weathering QUV & Xenon, up to 5000 hrs (ASTM G153 & ASTM G155)	No Detrimental Effect
Staining Transmission Fluid, Antifreeze, Windshield Washing Fluid & Used Motor Oil, Ketchup, Mustard (ASTM E313-98)	Resilient
Acid Immersion 10% Sulfuric Acid, 72 hrs	No Detrimental Effect
Base Immersion 10% Sodium Hydroxide, 72 hrs	No Detrimental Effect