AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Austex Commercial Fabrics

PO Box 15

Sample Description

Thomastown VIC 3074

Test Number : 17-001836

Issue Date : 21/04/2017

29/06/2017

Print Date

Clients Ref : "Fusion"

Woven coated fabric
Colour: White
End Use: Upholstery

Nominal Composition: 90% Polyester, 10% Polyurethane

ASTM D5034-2009 Breaking Load & Elongation of Textile Fabric Using Grab Method

Instrument 5566

State of Tested Specimen Conditioned

Gauge Length 75.00000 mm

Cross Head Speed 300 mm/min

Size of Jaw Faces - Front 25 x 50 mm mm
Size of Jaw Faces - Back 50 x 75 mm mm

Test G-F

	Machine Direction	Cross Direction	
Mean Breaking Force	2000	2000	N
Mean Apparent Elongation at Break	53.3	53.3	%
No. of Specimens tested	5	6	
Minimum Mean value	1700	1970	N
Maximum Mean value	2070	2070	N
Minimum Mean Elongation at Break	50.0	51.7	%

96373 18811 Page 1 of 1

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Chemical Testing

Mechanical Testing

- Performance & Approvals Testing

: Accreditation No.

: Accreditation No.

983

: Accreditation No. 1356

lless otherwise stated. AWTA

mples. The above test results

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons)