

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Wortley Group Pty Ltd
25 Geddes Street
Mulgrave VIC 3170

Test Number : 17-007102
Issue Date : 11/01/2018
Print Date : 12/01/2018

Sample Description Clients Ref : "Lure Fig"
Woven coated upholstery fabric
Nominal Composition : 100% Polyester
Nominal Mass per Unit Area/Density : Approx: 396g/m2
Nominal Thickness : Approx: 1mm

AS/NZS 1530.3-1999

Methods for Fire Tests on Building Materials, Components and Structures Part 3: Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

Face tested:	Face		
Date tested:	10/01/2018		
	Standard Error		Mean
Ignition time	0.18		8.35 min
Flame propagation time	Nil		Nil sec
Heat release integral	3.7		96.4 kJ/m ²
Smoke release, log d	0.0519		-0.7865
Optical density, d			0.1696 / metre
Number of specimens ignited:			6
Number of specimens tested:			6
Regulatory Indices:			
Ignitability Index			12 Range 0-20
Spread of Flame Index			0 Range 0-10
Heat Evolved Index			3 Range 0-10
Smoke Developed Index			5 Range 0-10

116415

24581

Page 1 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Wortley Group Pty Ltd
25 Geddes Street
Mulgrave VIC 3170

Test Number : 17-007102
Issue Date : 11/01/2018
Print Date : 12/01/2018

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

116415

24581

Page 2 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No. 983
: Accreditation No. 985
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR