

(i) Check local VOC regulations to ensure compliance of all products in your area.

DESCRIPTION

Rubberized Undercoating and **Low VOC Rubberized Undercoating** are premium, paintable, textured coatings for sound dampening, chip resistance, rust protection and corrosion protection.

FEATURES

- Sound-dampening properties
- Chip and corrosion resistant
- · Paintable without bleed through
- Fast-drying
- Uniform final appearance
- Aerosol includes straw for tight spots
- Quality asphalt free formula

SUITABLE SUBSTRATES

• Properly prepped and primed surfaces

TYPICAL PROPERTIES

Part:	Product Name:	Color:	Container:	
39513	Rubberized Undercoating (Europe Only)	White	Aerosol	
39523	Rubberized Undercoating	Black	Aerosol	
40523	Low VOC Rubberized Undercoating	Black	Aerosol	
40524	Low VOC Rubberized Undercoating	Black	Quart	

	Regulatory	Actual	EU	%
VOC 39513	588 g/L, 4.90 #/gal	588 g/L, 4.90 #/gal	588 g/L	71%
VOC 39523	572 g/L, 4.77 #/gal	572 g/L, 4.77 #/gal	572 g/L	66%
VOC 40523	468 g/L, 3.90 #/gal	348 g/L, 2.90 #/gal	598 g/L	< 40%
VOC 40524	429 g/L, 3.57 #/gal	318 g/L, 2.65 #/gal	666 g/L	N/A

Paintable:

Yes

HANDLING AND APPLICATION

PREPARATION:

1. Clean surface with SEM Solve or Zero VOC Surface Cleaner. Remove any loose paint, rust, oil and grease.

2. Blow off and clean again with SEM Solve or Zero VOC Surface Cleaner.

APPLICATION:

AEROSOL:

Distance:	6-8"
Coats:	2-3 medium wet
Flash time:	3-5 minutes
Top Coat time:	30 minutes

Note:

When utilizing any **Rubberized Undercoating** product over 1K coatings, softening or separation may occur. Test in an inconspicuous area for compatibility.

Note:

If clogging develops, remove spray button with a twisting motion and clean with **XXX Gun Cleaner** or material compliant with VOC regulations in your area. Do not stick pin or other object into can. Gently replace spray button with top of can and spray button pointed away from you.

After each use, turn can upside down and spray several seconds to clear spray tip.

BULK:

1. Attach Low VOC Rubberized Undercoating to Economy Coating Gun or Premium Undercoat Gun.

2. Using 35-40 psi, apply 2-3 medium coats, allowing 3-5 minutes flash time between coats.

Note:

When utilizing any **Rubberized Undercoating** product over 1K coatings, softening or separation may occur. Test in an inconspicuous area for compatibility.

Note:

Clean gun immediately after use with solvent compliant in your area. Final texture, flash times, and dry times are affected by gun distance, air pressure, temperature, and humidity.

STORAGE:

Rubberized Undercoating and **Low VOC Rubberized Undercoating** should be stored in a cool, dry place with adequate ventilation away from heat, sparks and flames. The shelf life for **Rubberized Undercoating** and **Low VOC Rubberized Undercoating** is 3 years when stored under normal conditions.

Part:	Product Name:	Size:		
38371	SEM Solve	Gallon		
38373	SEM Solve	20 oz. Aerosol		
38374	SEM Solve	Quart		
38375	SEM Solve	5 Gallon		
40401	Zero VOC Surface Cleaner	Gallon		
40404	Zero VOC Surface Cleaner	Quart		
77743	XXX Gun Cleaner	20 oz. Aerosol		
71101	Economy Coating Gun	1 Each		
71109	Premium Undercoat Gun	1 Each		

RELATED PRODUCTS:

Technical Consultation Service

Our Technical Staff is ready to assist you with any questions. You are invited to take advantage of our extensive experience, laboratory services and trained field service representatives. Call (800) 831-1122 for answers to your questions. Hours of operation are Monday through Thursday 8:00 am until 5:00 pm EST and on Friday 8:00 am until 4:30 pm EST.

Disclaimer:

The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed. All users of the materials are responsible for assuring that it is suitable for their needs, environment and use. All data subject to change as SEM deems appropriate.

Users should review the Safety Data Sheet (SDS) and product label for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the SDS and product label are available upon request.