

# Elegance Velvet

## Product Description

A gently textured, bright-white matte fine art paper. Capable of generous saturation and D-max rivaled only by our flagship fine art papers. Soft and tactile, Elegance Velvet is acid and lignin free. Certified 100+ years archival by an independent third party.



## Physical Specifications

Base Composition	100% Cotton Rag
Basis Weight	300 gsm
Caliper	.18 mils
Opacity	.97%
Gloss	2 GU
CIE L*a*b* (F7/2)	L*98.1 / a* 3.0 / b* (-5.5)
Texture	.Delicate
Finish	Bright White Matte
Core Diameter	.3"



## Printer Compatibility & Handling

Aqueous Piezo Printer Compatibility . . . . . Epson®, Roland® Mutoh®, Mimaki®

Aqueous Thermal Printer Compatibility . . . . . Canon®, HP® ColorSpan®, Encad Novajet®

Solvent Printer Compatibility . . . . . N/A

Ink Compatibility . . . . . All Dyes & Pigments

Optimal Print Environment . . . . . 70°F (21°C), 30-60% Relative Humidity

**Handling:** Avoid touching the coated surface. Cotton gloves should be used when handling inkjet coated materials from Breathing Color.

**Note:** Coated surface of every roll faces out.

## Additional Information

Storage . . . . . 70°F (21°C) / 50% Relative Humidity; store in original packaging and in a controlled environment

Shelf Life . . . . . Minimum 1 year from purchase date, when stored as specified

Lamination . . . . . Not required

Print Settings & ICC Profiles . . . . . Custom ICC Profile will produce optimum results

**Note:** Actual print stability will vary according to media, printed image, display conditions, light intensity and atmospheric conditions. Breathing Color does not guarantee the longevity of prints. For maximum print life display all prints under glass or lamination or properly store them. All of the descriptive information and recommendations for the use of Breathing Color products should be used only as a guide. Furnishing such information and recommendations shall in no event constitute a warranty of any kind by Breathing Color. All purchasers of Breathing Color products shall independently determine the suitability of the material for the purpose for which it is purchased. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither the seller nor manufacturer shall be liable either in tort or in contract for any loss of damage, direct, incidental or consequential (including loss of profits or revenue) arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in agreement signed by officers of seller and manufacturer.