

119 Lurgan Ave, Suite C Shippensburg, PA 17257 PHONE: 717.300.1311

EMAIL: i@needrubbernow.com www.americanmaterialsupply.com





REINFORCED NEOPRENE

NAME: NEOPRENE CLOTH INSERTED

RUBBER: POLYCHLOROPRENE - CLOTH INSERT: NYLON

Fuel Resistance: GOOD

Tear Resistance: EXCELLENT Solvent Resistance: GREAT Oil Resistance: GREAT

Oli resistance. Ortexi

Aging Weather / Sunlight: FAIR

<<< RESISTANCE

65 DUROMETER
Tensile Strength: 820 psi
Elongation Max: 200%
SURFACE: SMOOTH
NYLON INSERT FOR EXTRA STRENG
Rubber Temperature: -20 F° to 170 F°

***Our rubber products are blended of various polymers formulated to meet stated physical specifications.

Recommendations made by American Material Supply in its product literature relating to applications of the rubber are believed to be reliable, but we make no warranty of results to be obtained since the conditions of the end application by Buyer and others are beyond American Material Supply's control.***