

# CP Tex

Diazo sensitized direct emulsion for use with discharge, water-based and plastisol inks.

## CP Tex

- Shoots fast with high resolution
- Extremely durable, yet reclaimable with high pressure washer
- Excellent water resistance
- High solids content (42% sensitized)
- Excellent coatability on a variety of mesh counts

*CP Tex diazo-based direct emulsion is easy to use with excellent resolution and high definition.*



### MATERIALS REQUIRED

Exposure unit  
Washout sink  
Clean work area  
Scoop coater

### RECOMMENDED

Drying cabinet  
Pressure washer

### CHEMICALS REQUIRED

Chroma/Clean™ mesh degreaser  
Chroma/Strip™ screen reclaimant

### RECOMMENDED

Chroma/Haze™ haze remover

### SAFETY AND HANDLING

CP Tex emulsion should be handled like any other direct emulsion. This material is not hazardous when used within reasonable standards of industrial hygiene and safe working practices. Refer to MSDS.

### STANDARD SIZES

Quart, gallon, 3.5 gallon, 50 gal. drum

### SPECIFICATIONS

Appearance: light violet  
Solids: 43.8% (before sensitized)  
Exposure: fast (see reverse)  
Other: suitable for standard water-based inks

### STORAGE

**Expiration date.** Always check expiration date on sensitizer bottle to assure freshness.

**Sensitized CP Tex emulsion** has a shelf life of 3-4 weeks when stored at room temperature.

**Coated, unexposed screens** can be stored up to 2-3 weeks in a clean, cool, dry and completely dark area.



## Chromaline Screen Print Products

4832 Grand Ave. Duluth, Minnesota 55807 Tel: 218-628-2217 Fax: 218-628-3245  
Web Site: [www.chromaline.com](http://www.chromaline.com) E-mail: [sales@chromaline.com](mailto:sales@chromaline.com)

# CP Tex



## INSTRUCTIONS

### DEGREASE

Using Chroma/Clean™ mesh degreaser, work up a lather on both sides of mesh. Flood screen and frame thoroughly with garden type hose, then dry.




### MIX

Mix the emulsion and sensitizer according to the instructions on the bottle. To reduce air bubbles, let the emulsion stand at least 2 hours (preferably overnight) before using.


### COAT

Begin with room temperature emulsion. Using a scoop coater, slowly apply the first coat to the print side. Then coat the squeegee side and dry. If a thicker stencil is required, additional coats may be applied to the print side. Dry thoroughly between coats.




### DRY

Thoroughly dry screen in horizontal position, print side down, using a totally dark, clean drying cabinet. Temperature should not exceed 110°F (43°C).



### EXPOSE

Place emulsion side of photo-positive in contact with print side of screen. Exposure times for CP Tex will vary depending on your setup. See exposure guidelines at right for estimated exposure times.



### DEVELOP

Spray both sides of screen with lukewarm water, wait 30 seconds then wash print side of the screen until image is fully open. Rinse both sides thoroughly and place in dryer to dry. You are ready to print. Note: To speed development, use higher water pressure.



### RECLAIM

Apply Chroma/Strip screen reclaimer to both sides of screen. Scrub with a stiff nylon brush to ensure entire surface is wet; let it work a few moments until stencil begins to dissolve. Remove stencil residue with pressure washer, then rinse with garden type hose, thoroughly flooding screen and frame.



### EXPOSURE GUIDELINES

Note: Exposure times are suggested only as a guide. Use the step exposure method to determine optimal exposure times. Individual exposure times may vary depending upon equipment used, bulb age, and other shop conditions.

#### Exposure, 5k Metal Halide @ 40" (100 cm)

Mesh	Estimated Time
230 tpi/90 tpc	30-60 sec
110 tpi/43 tpc	60-90 sec

#### Exposure, 20 Watt Cool White Fluorescent @ 4" (10 cm)

Mesh	Estimated Time
230 tpi/90 tpc	9-12 min.
110 tpi/43 tpc	12-15 min.

Diazo based CP Tex works best with an exposing unit of high spectral output that peaks in the UV range of 350 to 420 nanometers (nm); 370 is optimal. Screens were coated 1x2 on yellow mesh.

We do not recommend grow lights.

**For Technical Service**  
**Call Toll Free 1-800-328-4261**  
**(Outside North America Call +1-218-628-2217)**  
**Email: [help@chromaline.com](mailto:help@chromaline.com)**