

Recommendations	
Product Overview	
Product Code	ES0000
Industry	Inks
Application	Screen Printing
Category	Specialty Inks
Chemistry	Plastisol
Substrate(s)	Cotton
Best Used By	12 months
Certification(s)	ISO9001
Curing:	
Fusion Temperature	320 °F
Gel Point	160 °F
Performance:	
Viscosity	Low
Coverage	Clear
After Flash Tack	Low
Squeegee:	
Squeegee Profile	Square
Squeegee Type	Polyurethane
Squeegee Speed	High
Screen:	
Mesh	230
Emulsion Type	Capillary film, Direct, Indirect
Cleanup	Bio-degradable screen wash
Storage:	
Storage Temperature	65°F - 95°F (18°C - 35°C)
Storage Notes	Avoid direct sun.

Last Change: Feb 2017

NPT ULTRA SOFT PRIMER CLEAR

ES0000 NPT Ultra Soft Primer Clear is designed to simplify stocking of multiple base plastisols. It functions as a multi-purpose product that gives you the ability to make subdued, soft hand colors on dark garments and extremely bright soft hand colors on lights. NPT Ultra soft Primer Clear is not a low bleed plastisol; therefore, it is not recommended for use on polyester/cotton dark fabrics. Mix with M3 colors to reduce opacity and increase color clarity for light color garments. Mix with high tack plastisols to reduce tack and increase flow. Use as a "lint catcher", in the first position for un-interrupted production runs when printing on dark 100% cotton. Excellent penetration into fiber when printing with fine mesh.

Features

- Non-Phthalate formulation to comply with new regulations restricting phthalates.
-
-
-

Instructions

• **Extender Base** (reduce opacity and increase color clarity) Mix with opaque colors to reduce cost, opacity and increase color clarity. Extending colors also increases ink volume and decreases cost. • **Curable thinner** (reduce viscosity, increase flow) Mix with other NPT plastisol colors to reduce viscosity and allow ink to flow into the mesh opening. • **Lint Catcher for dark fabrics** (uninterrupted production) Create a single clear plate by combining all colors in an image to be printed on a dark 100% cotton fabric. Print Primer Clear (230 mc in (90 mc cm) or higher mesh and then flash. Follow with all other colors in the design. ES0000 primes the fiber by pre-wetting prior to the application of the white underlay. Much of the lint that is normally attracted to the back of the white screen is picked up on the back of the primer clear screen, which allows for un-interrupted production runs. • **Overcoat Clear** to reduce fibrillation Create a single clear plate by combining all colors in an image to be printed on 100% cotton. Print all colors, flash, then print NPT Ultra Soft Primer Clear (230 mc in (90 mc cm) over the top to seal fibers, reducing the amount of fibrillation seen after wash and dry cycles. Note: Avoid over printing colors formulated with the 4449 yellow used in Rutland mixing systems as some color migration could result.

Recommendation

Do not dry clean, bleach, or iron the printed image. Note: This is not a low bleed ink. Do not print on polyester fabrics.

Statement

Rutland Plastic Technologies does not knowingly add plasticizers containing the phthalates listed and outlined in California Bill 1108, CPSIA HR-4040 and Oeko-tex Standard 100. The plasticizers identified may include di-(2-ethylhexyl) phthalate (DEHP), dibutyl phthalate (DBP), benzyl butyl phthalate (BBP), diisononyl phthalate (DINP), diisodecyl phthalate (DIDP), di-n-octyl phthalate (DnOP), (DIBP) Di-isobutyl, and (DMP) Dimethylphthalate, including esters of ortho-phthalic acid and are not direct ingredients in the manufacture of Clairra High Opacity Non-Phthalate Inks. Rutland Plastic Technologies does not test the final product for amounts of the aforementioned phthalate plasticizers and esters and encourages all users to conduct testing for their intended use.

Disclaimer:

Not all Rutland products are available in every country. Please check with your local representative for availability. The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.