

PRODUCT SPECIFICATION

8872

Binder	Polyurethane
Colour	Natural
Cork Granule Size	2/4 mm

TEST METHOD	PROPERTY	UNIT	VALUE
ISO 7322	Specific weight	Kg/m ³	230 - 300
ISO 7322	Tensile strength	kPa	≥ 400
ISO 7322	Compressibility	%	10– 30
ISO 7322	Recovery	%	≥ 65
ISO 7322	Boiling water	-	No disaggregation

PDA03329/1