

1. IDENTIFICATION

Grade	Broken Cork F-TYPE 3/30-35 mm
Scope	Describe product physical properties
Product Description	Broken Cork with 3/30-35 mm

2. PHYSICAL PROPERTIES

	Specification	Norm
Bulk Density (kg/m³)	150/200	ISO 2031
Moisture Content (%)	14 % (according contract terms)	ISO 2190
Sizes Analysis by mechanical sieving (% of retention)	ASTM Sieves	
	(mesh)	(mm)
	UP 5/16"	UP 8,00
	5	4,00
	6	3,35
	UNDER	0 - 10
	% Retention	ISO 2030
	30 - 70	
	10 - 20	
	1 - 10	
	0 - 10	

3. INSPECTION AND TEST PLAN

Equipment/Operation	Properties under control		
	Density (Kg/m ³)	Moisture Content (%)	Granulometric Distribution (%)
Densimetric machines	Once per hour	Once per hour	Once per 2 hours
Lot Formation (Bags of 35kg)	10 Bags (each)	10 Bags (each)	20 Bags (each)
Lot Formation (Bags from 75kg up and bales from 65kg up)	5 Bags (each)	5 Bags (each)	15 Bags (each)

4. OBSERVATIONS

Throughout the process the operator must be aware of the visual aspect of the granulated cork, in particular the existence of contaminants. Label color on the package and on the bag to be used accordingly to the costumer offer.

Date : 15/09/2022