



Industrial Mineral Services

DATA SHEET

SILICA FLOUR – HIM 2

SiO₂	99.7% typical
Al₂O₃	0.1% typical
TiO₂	0.02% typical
Fe₂O₃	0.03% typical
CaO	0.006% typical
K₂O	0.01% typical
Na₂O	0.006% typical

Granulometry

Residue on 53µm	2,5% typical
d50:-	17µm typical
Moisture:-	<1.0%

SiF HIM2 20-08-2014