

## ALUMINA HYDRATE

Al <sub>2</sub> O <sub>3</sub>	99.60%
Na <sub>2</sub> O	<0.04%
Moisture	<0.03%
Loss on ignition	34.50% typical
d10	1.5 – 3.5 micron
d50	9.0 – 12.0 micron
d90	18.0 – 26.0 micron