

Replaceable Cast in Place Specifications

Part No.	Standard Sizes	Weight	Box Quality	Anchors Included
ACC-R-1212-XX	1' X 1'	5 lbs. (2 kg)	10	4
ACC-R-2424-XX	2' X 2'	9 lbs. (4 kg)	10	9
ACC-R-2436-XX	2' X 3'	12 lbs. (5 kg)	10	12
ACC-R-2448-XX	2' X 4'	13 lbs. (7 kg)	10	13
ACC-R-2460-XX	2' X 5'	18 lbs. (9 kg)	10	18
ACC-R-3648-XX	3' X 4'	24 lbs. (11 kg)	10	18
ACC-R-3660-XX	3' X 5'	31 lbs. (13 kg)	10	24
ACC-R-3024CRV	30" X 24" 15' Radius	10 lbs. (4 kg)	10	9
ACC-R-ANCH	Anchor Assembly		50	
BIT-T27	T-27 tamper Proof Torx® Bit		5	

Replaceable Cast in Place Physical Characteristics

ASTM Reference	Test Description	Test Results
ASTM D 695	Compressive Strength	26,900
ASTM D 790	Flexural Strength	31,300
ASTM D 570	Water Absorption	0.05%
ASTM C 1028	Slip Resistance	1.18 Dry / 0.88 wet
ASTM E 84	Flame Spread Index	<= 25
ASTM B 117	Salt Spray	No Change (300 hours)
ASTM 1308	Chemical Stain	No Effect
ASTM C 501	Abrasion Resistance	lw >500
ASTM G 155	Accelerated Weathering	Delta E <5 (2,000 hours)
ASTM D 638	Tensile Strength	12,800 psi
AASHTO-H20	Load Bearing at 10,410 lbs	No Cracking, Delamination or Deformation
ASTM C 1026	Freeze/Thaw/Heat	No Chipping, Cracking, or Peeling
ASTM D 1037	Accelerated Aging (Freeze/Thaw)	No Changing in Color, Gloss or Delamination
ASTM D 696-03	Linear Thermal Expansion	9.45×10 ⁻⁷ per °Fahrenheit
RCRA-C	Non-Hazardous Classification	Non-Hazardous