


Geotextiles | Erosion Control | Geogrids | Geomembranes



Carthage Mills' FX-35HS is a multipurpose nonwoven geotextile made of polypropylene staple fibers which are formed into a random network, needlepunched and heatset for dimensional stability. FX-35HS is part of the Carthage **FX-HS Series** of nonwoven geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

AASHTO M 288: FX-35HS exceeds the geotextile requirements for Temporary Silt Fence (NONWOVEN - SUPPORTED).

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
☐ Mechanical			
Grab Tensile Strength	ASTM D 4632	0.40 kN	90 lbs
Grab Tensile Elongation	A31M D 4032	50%	
Trapezoidal Tear	ASTM D 4533	0.18 kN	40 lbs
CBR Puncture	ASTM D 6241	1.11 kN	250 lbs
□ Endurance			
UV Resistance	ASTM D 4355	70% @ 500 hrs	
☐ Hydraulics / Filtration			
Permittivity ⁽¹⁾	- ASTM D 4491	2.00 sec ⁻¹	
Water Flow Rate (1)	A31M D 4431	5908 lpm/m ²	145 gpm/ft²
Apparent Opening Size (AOS) (1, 2)	ASTM D 4751	0.300 mm	50 US Std. Sieve
□ Physical			
Mass Per Unit Area (Typical)	ASTM D 5261	118.65 g/m²	3.5 oz/yd ²
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	3.81 m x 109.7 m 418.1 m ² 54 kg	12.5 ft x 360 ft 500 yd² 120 lbs
		4.57 m x 109.7 m 501.6 m ² 72.5 kg	15.0 ft x 360 ft 600 yd ² 160 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

- (1) At the time of manufacturing. Handling, storage and shipping may change these properties.
- (2) Maximum Average Roll Value
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-23 and are subject to change without notice.

» AASHTO M 288: Geotextile Product Selection Guide

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.