

Surface Applied Tiles

Surface Applied Specifications

Part No.	Standard Sizes	Weight	Box Quantity	Anchors
ACC-S-1212-XX	1' X 1'	2 lbs. (1 kg)	16	4
ACC-S-2424-XX	2' X 2'	8 lbs. (4 kg)	16	6
ACC-S-2436-XX	2' X 3'	10 lbs. (5 kg)	16	8
ACC-S-2448-XX	2' X 4'	13 lbs. (6 kg)	16	8
ACC-S-2460-XX	2' X 5'	16 lbs. (7 kg)	16	10
ACC-S-3648-XX	3' X 4'	20 lbs. (9 kg)	16	12
ACC-S-3660-XX	3' X 5'	27 lbs. (12 kg)	16	15
ACC-S-3024-CRV	30" X 24" 15' Radius	8 lbs. (4 kg)	16	16
ACC-S-ANCH-XX	Axius® Fasteners		50	
TBS-010	Tactile Bond & Seal		12	

Surface applied Physical Characteristics

ASTM Reference	Test Description	Test Results
ASTM D 695	Compressive Strength	26,900
ASTM D 790	Flexural Strength	31,300
ASTM D 570	Water Absorption	0.05%
ASTM C 1028	Slip Resistance	1.18 Dry / 0.88 wet
ASTM E 84	Flame Spread Index	<= 25
ASTM B 117	Salt Spray	No Change (300 hours)
ASTM 1308	Chemical Stain	No Effect
ASTM C 501	Abrasion Resistance	lw >500
ASTM G 155	Accelerated Weathering	Delta E <5 (2,000 hours)
ASTM D 638	Tensile Strength	12,800 psi
AASHTO-H20	Load Bearing at 10,410 lbs	No Cracking, Delamination or Deformation
ASTM C 1026	Freeze/Thaw/Heat	No Chipping, Cracking, or Peeling
ASTM D 1037	Accelerated Aging (Freeze/Thaw)	No Changing in Color, Gloss or Delamination
ASTM D 696-03	Linear Thermal Expansion	9.45×10 ⁻⁷ per °Fahrenheit
ASTM C 1583	Tile Bond Strength	Passed
RCRA-C	Non-Hazardous Classification	Non-Hazardous