## CSG Sand Lab Dry Screened Test: (a) Grading

Supplier: Cardigan Sand & Gravel Co. Ltd.

Cnwc-y-Saeson Production Plant Penparc, Cardigan, Ceredigion SA43 1RB Material Description: 0/4 Lime Mortar Sand for Dubbing Out,

Stipple Coats, Base Coats & Rough Finishing Coats using Natural Hydraulic Lime NHLA (BLM Grey) 0/4 Plastering and Rendering Mortar Sand MP

Material Tested: 0/4 Plaster Fines Content: Category 1

BSI Published Document: PD 6682-3:2003 Tb1 B1 European Standard: BS EN 13139:2013(E)

Material Source: CYE/CSG NHLA 0/4 - 18/07/14

Aggregate Type: Glacial
Sampling Point: Cnwc-y-Saeson
Age: Pleistocene

7.907 . 10.01000.

Sampled by: DGK

Tel. No.: (01239) 612342 / 612560

Fax. No.: (01239) 615238

E-Mail: quarry@cardigansand.co.uk
Web: www.cardigansand.co.uk

Grid Ref.: SN 200E 485N

The results of the sieve analysis are as shown on those of the following sieves which have the retained weight recorded against them

recorded against them											
Sieve Size	Weight	%	%								
	Retained			Target	Tolerance						
(mm)	(g)	Retained	Passing	Grading							
14.000		0.0	100.0	100.0							
10.000	0.0	0.0	100.0	100.0							
8.000		0.0	100.0	100.0	100/100						
6.300	0.0	0.0	100.0	100.0	98/100						
5.000		0.0	100.0	100.0							
4.000	2.0	0.6	99.4	100.0	89/99						
3.350*	0.0	0.0	99.4	100.0							
2.800	19.0	5.4	94.0	98.0							
2.000	41.5	11.9	82.1	95.0							
1.180	67.2	19.2	62.9	86.0							
1.000	21.3	6.1	56.8	85.0	± 20 45/85						
0.600	47.2	13.5	43.3	66.0							
0.500	15.0	4.3	39.1	55.0	MP 30/70						
0.425											
0.300	32.5	9.3	29.8	31.0							
0.250	11.1	3.2	26.6	25.0	± 20 10/50						
0.212	20.5	5.9	20.7	21.0							
0.150	61.3	17.5	3.2	11.0							
0.125	8.5	2.4	0.8	5.0	0/3						
0.075	1.9	0.5	0.2	0.0							
0.063	0.0	0.0	0.2	0.0	0/3						
0.000	0.8	0.2	0.0	0.0							
Total	349.8	100.0									

## For your information

Cardigan Sand & Gravel Co. quarries a deposit that was laid down by an ancient lake fed by rivers flowing off the tip of the Teifi glacier. Our sands and aggregates are the result of disintegration of rock during transportation by the glacier. Our products, therefore, contain negligible amounts of shell and salt.


Our extracted materials pass through a rigourous system of scrubbers, screens, over-spill weirs, cyclones (prewash and dewatering) and classifiers. This allows us to carefully select particle sizes for optimum performance and also removes organic materials, clay, silt and mineral salts from the product.


NHLA is the name we give to our Sand for Dubbing Out, Stipple Coats, Base Coats & Rough Finishing Coats using Natural Hydraulic Lime.

3mm down to 0.075mm particles may be used and the proportion retained on 0.150, 0.125 and 0.075 sieves should not exceed 15% in total.

Adapted from St Astier Natural Hydraulic Lime "Practical Guide to choosing Sands". E. & O.E.

* - Interpolated	Material	Clay	Silt		Sand			
			Fine Medium	Coarse	Fine	Medium	Coarse	
	microns	0-2	2-6 6-20	20-60	60-200	200-600	600-2000	





NOTE:- The % material larger than  $\,$  0.063mm but smaller than 0.125mm  $\,$ 

is recorded between the 0.063 and 0.125 grid lines, etc.

- 5 Grey columns exceeding 10% = very well graded
- 4 Grey colums exceeding 10% = well graded
- 3 Grey columns exceeding 10% = less well graded
- 2 Grey columns exceeding 10% = poorly graded
- 1 Grey column exceeding 10% = monogranular.

This information is a guide only and does not constitute a specification. There are a vast number of sands differing in grading and qualities. To be sure that a well graded sand is being used it is necessary that at least four grades form a substantial part of over 10% of the proposed sand. This sand has 5 grey columns in the size range above 10% indiciating a very well graded sand.