

MMA 330 Technical Data Sheet (TDS)

Description of Infinity Bond MMA 330

Infinity Bond MMA 330 is a 1:1 medium setting Methacrylate adhesive great for bonding difficult substrates like Fiberglass and hard to bond-to plastics. Infinity Bond MMA 330 offers excellent shock and impact resistance and holds up to extreme temperatures and thermal cycling.

Features of Infinity Bond MMA 330

- No Surface preparation required
- Excellent weathering properties
- Great shock and impact resistance
- Strong, structural bond
- 1:1 mix ratio - easy to dispense
- Excellent Thermal Cycling and Temperature Resistance

Properties of Infinity Bond MMA 330

Uncured

Viscosity @ 25°C (cps):

Resin.....40,000 – 80,000

Activator 80,000 – 120,000

ColorBlack, Cream or White

Mixed Density 8.60

Mix Ratio:

By Volume 1 to 1

By Weight 1 to 1

Thixotropic Index.....4 - 5

Flash Point..... 51°F

Cured

Shear Strength, psi.....1750-2800

Tensile Strength, psi 2500-3500

Work Time, Minutes 15-24

Handling Strength, Minutes.....30-45

Gap Fill, Inches: 0.25

Temperature Range -60F - +250F

MMA 330 Bonds To:

- | | |
|-------------------------|-----------------|
| • Aluminum | • Acrylics |
| • Steel | • ABS |
| • Stainless Steel | • Polycarbonate |
| • Coated Metals | • PPOs |
| • Fiberglass | • PVC |
| • Phenolics | • Vinyl |
| • Gel Coats | • Polystyrene |
| • Epoxy | • PBT Blends |
| • Rim Urethane | • PET Blends |
| • Polyurethane | |
| • Liquid Molding Resins | |

Application and Handling Guidelines

The product is best used at temperatures between 65 °F and 80 °F. Temperatures below 65 °F will slow the cure speed of the material and viscosities will be higher. Temperatures above 80 °F will cause the material to cure faster and viscosities will be lower. For consistent dispensing maintain temperature in the above mentioned range.

For optimum bond strength and to insure maximum performance in the finished assembly, join parts together within the specified work time of the adhesive. Make sure the bond joint has uniform coverage and that a sufficient amount of adhesive is in the bond area. It is important to have the adhesive applied, parts aligned and positioned, within the established work times for the product. To ensure maximum performance in the finished assembly parts should remain undisturbed until the fixture time is reached.

Clean up is best before the adhesive has cured. Cleaners containing acetone or Citrus terpene provide the best results. On cured adhesive repeat use may be required.

Precautions

Infinity Bond MMA 330 is flammable. Keep away from heat, spark, and open flames. KEEP OUT OF REACH OF CHILDREN. THE PRODUCT IS FOR INDUSTRIAL USE ONLY. Keep containers closed when not in use. Avoid contact with skin and eyes. Harmful if swallowed. Refer to Material Safety Data Sheet for complete safety information.

Storage and Shelf Life

The shelf life of the Infinity Bond MMA 330 is 12 months from date of shipment. Shelf life is based on the products being stored properly at temperatures between 55 °F and 75 °F. Exposure to temperatures above 75 °F will reduce the shelf life of these materials. These products should NEVER BE FROZEN.

Note

This data is furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is recommended that the product be tested in the application for which it is to be used.