

GLOSSIFY

CURING GUIDE

All Glossify Gel polishes should be cured on 90 seconds low heat mode.

The smart lamp has been designed to help reduce heat spikes, to ensure a full cure they must be cured for this length of time.

If Naturabuild gel feels wet and uncured it has been applied too thick. We recommend building in thin layers.

If the side of the thumbs feels uncured please ask your client to put them in separately holding the bottom of the lamp to ensure they stay in an upright position.

APPLYING THE GEL - GEL POLISH

1. Apply a thin coat of Basic Base or First Base. Seal the free edge and cure in a low heat lamp for 90 seconds.
2. Apply the first layer of gel polish, seal the free edge and cure for 90 seconds.
3. Apply the second layer of gel paint, seal the free edge and cure for 90 seconds.
4. Apply a coat of Glossy top and seal the free edge and cure for 90 seconds.
Glossy Top is no wipe.
5. Finish with a sparing drop of cuticle oil.

APPLYING THE GEL - NATURABUILD

1. Apply a thin base layer of Naturabuild. Seal the free edge and cure in a low heat lamp for 90 seconds.
2. Apply the second layer of Naturabuild, seal the free edge and cure for 90 seconds.
3. Apply the third layer of Naturabuild, seal the free edge and cure for 90 seconds.
4. Refine as desired and apply a coat of Glossy top, seal the free edge and cure for 90 seconds. Glossy Top is no wipe.
5. Finish with a sparing drop of cuticle oil.