


## WMP-VR PERFORATED

POLYPROPYLENE / SCRIM / KRAFT

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
White Film	Polypropylene	0.0015 inch	38.1 micron
Adhesive	Flame Resistant		
Reinforcing	Tri-directional Fiberglass/Polyester	5 / inch (MD) 4 / inch (XD)	20 / 100 mm (MD) 16 / 100 mm (XD)
Kraft	Natural	11 lbs / 3000 ft <sup>2</sup>	18 g / m <sup>2</sup>

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	17 lbs / 1000 ft <sup>2</sup>	83 g / m <sup>2</sup>
Permeance (WVTR)	ASTM E96 Procedure A	> 10 perm (grains/hr'ft <sup>2</sup> in Hg)	> 574 ng / N's
Bursting Strength	ASTM D774	55 psi	3.9 kg / cm <sup>2</sup>
Puncture Resistance	ASTM C1136	115 beach units	3.4 Joules
Tensile Strength	ASTM C1136	35 lbs/inch width (MD) 25 lbs/inch width (XD)	6.1 kN / m (MD) 4.4 kN / m (XD)
Caliper / Thickness	Micrometer	0.008 inch	203 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Light Reflectance	ASTM C523	85%	85%

FIRE TESTING	ASTM E84 / UL 723		
	Film Side	Kraft Side	
Flame Spread	10	15	
Smoke Developed	10	5	

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

**“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION**

5010 River Road Mount Bethel, Pennsylvania 18343-5610 U.S.A.  
Phone: (570) 897-8200 Fax: (570) 897-6081 Web: [www.lamtec.com](http://www.lamtec.com)