

**4+** ENGINEERED POLY SHEETING**VAPOR RETARDERS**DIVISION  
033000, 072600**PRODUCT NAME**

Nu-Age Films• 4+ Engineered Poly Sheeting

**MANUFACTURER****ISI BUILDING PRODUCTS**401 Truck Haven Road  
East Peoria, IL 61611  
866.698.6562 / [www.isibp.com](http://www.isibp.com)**PRODUCT DESCRIPTION****BASIC USE**

Nu-Age Films are uniquely enhanced high performance vapor retarders that exceed performance properties of conventional single layer polyethylene sheeting. Nu-Age Films 4+ surpasses 4-mil polyethylene sheeting requirements outlined in ASTM D 4397. Nu-Age Films are used as multi-purpose high performance vapor retarders for numerous construction, industrial and agricultural applications. Nu-Age Films 4+ delivers excellent impact resistance, tensile strength and elongation for demanding vapor retarder and protective covering applications.

**COMPOSITION & MATERIALS**

Nu-Age Films are tri-layer extruded films manufactured and engineered using a distinct virgin resin formulation. The tri-layer extrusion uses separate extruders to produce different layers of polymers. The layers join, in the liquid state, just before they are extruded. The tri-layer manufacturing is desirable as it takes the best properties of different resins and links them together. The film structure is then engineered to perform better than its individual parts. Nu-Age Films 4+ is a lighter weight roll with increased product performance all while maintaining long-term stability.

**SIZE**

Available in roll sizes ranging from 8 to 20 feet wide by 100 feet in length. Special roll lengths are available upon request.

**WEIGHT**

Approximately 6.24 lbs per 1,000 ft<sup>2</sup> at .0013 inches (33.02 μ) thick.

**BENEFITS**

- Unrivaled material solution
- Made from premium grade virgin resin
- Enhanced performance
- State-of-the-art one-of-a-kind technology
- Lighter weight for ease of installation
- Outperforms 4-mil poly per ASTM D 4397
- Multi-use for construction, industrial and agricultural applications
- Superior value without forfeiting quality

**TECHNICAL DATA****APPLICABLE STANDARDS**

**ASTM D 4937** Standard Specification for Polyethylene Sheeting for Construction, Industrial and Agricultural Applications

**ASTM D 2103** Standard Specification for Polyethylene Film and Sheeting

**ASTM D 1709** Standard Test Methods for Impact Resistance of Plastic Film by the Free-Falling Dart Method

**ASTM D 882** Standard Test Method for Tensile Properties of Thin Plastic Sheeting

**ASTM F 1249** Standard Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulate16d Infrared Sensor

**ASTM E 96** Standard Test Methods for Water Vapor Transmission of Materials

**ASTM E 1643** Standard Practice for Installation of Water Vapor Retarders Used in Contact with Earth or Granular Fill Under Concrete Slabs

NOTE: All Nu-Age Films are tested by accredited, third-party testing agencies following stringent industry guidelines and testing standards.

**ENVIRONMENTAL CONSIDERATIONS**

Nu-Age Films can aid in controlling soil gas, such as radon.

**PHYSICAL PROPERTIES**

Nu-Age Films 4+ exceeds 4-mil polyethylene sheeting performance properties outlined in ASTM D 4397.

**INSTALLATION**

Check with local building codes, ACI 302, ACI 360 and/or architectural/engineering specifications. Instructions on architectural or structural drawings should be reviewed and followed. Detailed installation instructions can be obtained by calling the manufacturer at 866.698.6562 or visiting [www.isibp.com](http://www.isibp.com).

## WARRANTY

Warranty information can be obtained by calling the manufacturer at 866.698.6562 or visiting [www.isibp.com](http://www.isibp.com).

## MAINTENANCE

Requires no maintenance once installed.

## TECHNICAL SERVICES

Technical information and detailed test results can be obtained by calling the manufacturer at 866.698.6562.

## FILING SYSTEMS

Additional information can be obtained by calling the manufacturer at 866.698.6562 or visiting [www.isibp.com](http://www.isibp.com).

PROPERTIES TEST PROCEDURE (INDEPENDENT TEST FACILITY)	TEST METHOD APPLICABLE STANDARDS	RESULTS IP UNITS
THICKNESS	N/A	.0012 in   33.02 $\mu$
PERFORMANCE CLASSIFICATION	ASTM D 4397	EXCEEDS 4-mil
FILM TYPE	ASTM D 2103	TYPE 15232
PUNCTURE RESISTANCE	ASTM 1709 METHOD A	211 grams
TENSILE STRENGTH	ASTM D 882	3,550 PSI LD   24.5 MPa 3,850 PSI CD   26.5 MPa
ELONGATION	ASTM D 882	610% LD, 710% CD
WATER VAPOR PERMEANCE	ASTM E 96 METHOD E	0.19 perms*   0.013 perms**
CHEMICAL RESISTANCE	N/A	UNAFFECTED
LIFE EXPECTANCY	N/A	INDEFINITE

\*grains/(ft<sup>2</sup>\*hr\*inHg) \*\*g/(m<sup>2</sup>\*24hr\*mmHg)

**DISCLAIMER:** TO THE BEST OF OUR KNOWLEDGE, THE SPECIFICATION CHART LISTS TYPICAL PROPERTY VALUES AND ARE INTENDED AS GUIDES ONLY, NOT AS SPECIFICATION LIMITS. ISI BUILDING PRODUCTS MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, NO GUARANTEE OF SATISFACTORY RESULTS FROM RELIANCE UPON CONTAINED INFORMATION OR RECOMMENDATIONS AND DISCLAIMS ALL LIABILITY FOR RESULTING LOSS OR DAMAGE.



AN AFFILIATE OF MEYER ENTERPRISES, LLC  
401 TRUCK HAVEN ROAD, EAST PEORIA, IL 61611  
PHONE: 309.698.0062 / FAX: 309.698.0065