



## SECTION 07210

### RIGID BOARD INSULATION

Display hidden notes to specifier. (Don't know how? [Click Here](#))  
*Copyright 2013 - 2013 ARCAT, Inc. - All rights reserved*

**\*\* NOTE TO SPECIFIER \*\* Rmax Operating, LLC; Roof and Wall Insulation.**

This section is based on the products of Rmax Operating, LLC., which is headquartered at:  
13524 Welch Rd..  
Dallas, TX 7524.  
Toll Free Tel: 800-527-0890.  
Tel: 972-387-4500.  
Fax: 972-387-4673.  
Email: [specs@rmax.com](mailto:specs@rmax.com).  
Web: <http://www.rmax.com>.

#### PART 1 GENERAL

##### 1.1 SECTION INCLUDES

**\*\* NOTE TO SPECIFIER \*\* Delete items below not required for project.**

- A. Polyisocyanurate insulation for sheathing and underlayment applications.
- B. Polyisocyanurate insulation for concrete and masonry wall applications.
- C. Polyisocyanurate insulation for cavity wall applications.

##### 1.2 RELATED SECTIONS

**\*\* NOTE TO SPECIFIER \*\* Delete any sections below not relevant to this project; add others as required.**

- A. Section 03300 - Cast In Place Concrete: Perimeter and under-slab insulation installation.
- B. Section 03300 - Cast In Place Concrete: Concrete base wall.
- C. Section 03400 - Pre-Cast Concrete: Pre-cast concrete base wall.
- D. Section 05400 - Cold Formed Metal Framing.
- E. Section 04210 - Clay Masonry: Brick facing.
- F. Section 04800 - Masonry Assemblies: Masonry base wall.

- G. Section 06100 - Rough Carpentry.
- H. Section 07260 - Vapor Retarders: Vapor retarder materials adjacent to insulation.
- I. Section 07270 - Air Barriers: Air seal materials adjacent to insulation.
- J. Section 09110 - Non-Structural Metal Framing.
- K. Section 09200 - Plaster and Gypsum Board.

### 1.3 REFERENCES

**\*\* NOTE TO SPECIFIER \*\* Delete references from the list below that are not actually required by the text of the edited section.**

- A. ASTM C209 - Standard Test Methods for Cellulosic Fiber Insulating Board.
- B. ASTM D1621 - Standard Test Method for Compressive Properties of Rigid Cellular Plastics.
- C. ASTM D1622 - Standard Test Method for Apparent Density of Rigid Cellular Plastics.
- D. ASTM D2126 - Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging.
- E. ASTM E2178 - Standard Test Method for Air Permeance of Building Materials.
- F. ASTM E 72 - Standard Test Methods of Conducting Strength Tests of Panels for Building Construction.
- G. ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials.
- H. ASTM E 96 - Standard Test Methods for Water Vapor Transmission of Materials.
- I. ASTM E 331 - Standard Test Method for Water Penetration of Exterior Windows, Skylights, Doors, and Curtain Walls by Uniform Static Air Pressure Difference.
- J. ASTM E 564 - Standard Practice for Static Load Test for Shear Resistance of Framed Walls for Buildings.
- K. ASTM E 2126 - Standard Test Methods for Cyclic (Reversed) Load Test for Shear Resistance of Vertical Elements of the Lateral Force Resisting Systems for Buildings.
- L. ASTM E 2357 - Standard Test Method for Determining Air Leakage of Air Barrier Assemblies.
- M. NFPA 285 - Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Non-Load-Bearing Wall Assemblies Containing Combustible Components.
- N. SBCRI Single Element Lateral Load Testing.
- O. UL 1715 - Fire Test of Interior Finish Material.

### 1.4 SUBMITTALS

- A. Submit under provisions of Section 01300.
- B. Product Data: Manufacturer's data sheets on each product to be used, including:
  - 1. Preparation instructions and recommendations.
  - 2. Storage and handling requirements and recommendations.
  - 3. Installation methods.

**\*\* NOTE TO SPECIFIER \*\* Delete selection samples if colors have already been selected.**

- C. Selection Samples: For each finish product specified, two complete sets of color chips representing manufacturer's full range of available colors and patterns.
- D. Verification Samples: For each finish product specified, two samples, minimum size 4 inches by 6 inches (102mm x 150 mm).

#### 1.5 QUALITY ASSURANCE

- A. Manufacturer Qualifications: All primary products specified in this section will be supplied by a single manufacturer with a minimum of ten (10) years experience.
- B. Installer Qualifications: All products listed in this section are to be installed by a single installer with a minimum of five (5) years demonstrated experience in installing products of the same type and scope as specified.

**\*\* NOTE TO SPECIFIER \*\* Include a mock-up if the project size and/or quality warrant taking such a precaution. The following is one example of how a mock-up on a large project might be specified. When deciding on the extent of the mock-up, consider all the major different types of work on the project.**

- C. Mock-Up: Provide a mock-up for evaluation of surface preparation techniques and application workmanship.
  - 1. Finish areas designated by Architect.
  - 2. Do not proceed with remaining work until workmanship, color, and sheen are approved by Architect.
  - 3. Refinish mock-up area as required to produce acceptable work.
- D. Pre-installation Meeting: Conduct pre-installation meeting to verify project requirements, foundation/structural system/substrate conditions, and insulation manufacturer's installation instructions.

#### 1.6 DELIVERY, STORAGE, AND HANDLING

- A. Store products per manufacturer's instructions until ready for installation.
- B. Store and dispose of hazardous materials, and materials contaminated by hazardous materials, in accordance with requirements of local authorities having jurisdiction.

#### 1.7 SEQUENCING

- A. Ensure that locating templates and other information required for installation of products of this section are furnished to affected trades in time to prevent interruption of construction progress.
- B. Ensure that products of this section are supplied to affected trades in time to prevent interruption of construction progress.

#### 1.8 PROJECT CONDITIONS

- A. Maintain environmental conditions (temperature, humidity, and ventilation) within limits recommended by manufacturer for optimum results. Do not install products under environmental conditions outside manufacturer's absolute limits.

## 1.9 WARRANTY

- A. At project closeout, provide to Owner or Owners Representative an executed copy of the manufacturer's standard limited warranty against manufacturing defect, outlining its terms, conditions, and exclusions from coverage.

## PART 2 PRODUCTS

### 2.1 MANUFACTURERS

- A. Acceptable Manufacturer: Rmax Operating, LLC, which is located at: 13524 Welch Rd. ; Dallas, TX 75244-5227; Toll Free Tel: 800-527-0890; Tel: 972-387-4500; Fax: 972-387-4673; Email: [request info \(rmax@rmax.com\)](mailto:request info (rmax@rmax.com)); Web: [www.rmax.com](http://www.rmax.com)
  - 1. Rmax Operating, LLC; 13524 Welch Rd., Dallas, TX 75244. Toll Free Tel: 800-527-0890. Tel: 972-387-4500. Fax: 972-387-4673. Email: [specs@rmax.com](mailto:specs@rmax.com). Web: [www.rmax.com](http://www.rmax.com) .
  - 2. Rmax Operating, LLC; 210 Lyon Dr., Fernley, NV 89408. Toll Free Tel: 800-762-9462. Tel: 775-575-4849. Fax: 775-575-5035. Email: [specs@rmax.com](mailto:specs@rmax.com). Web: [www.rmax.com](http://www.rmax.com) .
  - 3. Rmax Operating, LLC; 1649 S. Batesville Rd., Greer, SC 29650. Toll Free Tel: 800-845-4455. Tel: 864-297-1382. Fax: 864-234-7548. Email: [specs@rmax.com](mailto:specs@rmax.com). Web: [www.rmax.com](http://www.rmax.com) .

**\*\* NOTE TO SPECIFIER \*\* Delete one of the following two paragraphs; coordinate with requirements of Division 1 section on product options and substitutions.**

- B. Substitutions: Not permitted.
- C. Requests for substitutions will be considered in accordance with provisions of Section 01600.

### 2.2 CONTINUOUS INSULATION SOLUTIONS FOR WALLS

- A. ECOMAXci Wall Solution: Exterior continuous insulation solution for commercial walls including board insulation, tape, and flashing to provide continuous thermal and moisture protection of the vertical building exterior.
  - 1. Fire Performance in accordance with NFPA 285.
  - 2. Air Performance in accordance with ASTM E2357.
  - 3. Water Resistance Performance in accordance with ASTM E331.

**\*\* NOTE TO SPECIFIER \*\* Select Insulation. Delete four of the next five paragraphs.**

- 4. Continuous Insulation: ECOMAXci - Thickness/R Value: 1.0 inches (25mm)/R-6.5.
- 5. Continuous Insulation: ECOMAXci - Thickness/R Value: 1.5 inches (38mm)/R-10.
- 6. Continuous Insulation: ECOMAXci - Thickness/R Value: 2.0 inches (51mm)/R-13.1.
- 7. Continuous Insulation: ECOMAXci - Thickness/R Value: 2.5 inches (64mm)/R-16.7.
- 8. Continuous Insulation: ECOMAXci - Thickness/R Value: 3.0 inches (76mm)/R-20.3.

**\*\* NOTE TO SPECIFIER \*\* Flashing Tape(s) required for solution.**

- 9. Flashing Tape: R-SEAL 3000.
- 10. Flashing Tape: R-SEAL 6000.

**\*\* NOTE TO SPECIFIER \*\* Select Cavity Insulation Type. Delete three of the next four paragraphs.**

11. Cavity Insulation: Glass fiber batt Insulation; faced.
12. Cavity Insulation: Glass fiber batt Insulation; unfaced.
13. Cavity Insulation: Noncombustible insulation as specified in another section.
14. Cavity Insulation: None.

- B. Thermasheath-SI Wall Solution: Exterior continuous insulation solution for residential walls including structural insulation board, tape, and flashing to provide continuous thermal and moisture protection of the vertical building exterior.
1. Structural Performance in accordance with ASTM E72.
  2. Structural Performance in accordance with ASTM E564.
  3. Structural Performance in accordance with ASTM E2126.
  4. Structural Performance in accordance with SBCRI Single Element Lateral Load testing.

**\*\* NOTE TO SPECIFIER \*\* Select Insulation. Delete two of the next three paragraphs.**

5. Insulation: Thermasheath-SI - Thickness/R Value: 0.5 inches (13mm)/R-3.2.
6. Insulation: Thermasheath-SI - Thickness/R Value: 0.75 inches (19mm)/R-5.0.
7. Insulation: Thermasheath-SI - Thickness/R Value: 1.0 inches (25mm)/R-6.0.

**\*\* NOTE TO SPECIFIER \*\* Select Flashing Tape. Retain only those required on the project.**

8. Flashing Tape: R-SEAL 3000
9. Flashing Tape: R-SEAL 6000.

**\*\* NOTE TO SPECIFIER \*\* Retain only insulation types required on the project and delete all others.**

## 2.3 CONTINUOUS INSULATION FOR WALLS

- A. ECOMAXci: Closed-cell polyisocyanurate insulation with a 12mil glass fiber reinforced foil facer on one side and a 10mil glass fiber reinforced foil facer on the other side.
1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
  2. Compressive Strength in accordance with ASTM D1621: 25 psi.
  3. Flame Spread in accordance with ASTM E84: 25 or less.
  4. Smoke Developed in accordance with ASTM E84: 450 or less.
  5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
  6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
  7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
  8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

9. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.5.
10. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 10.0.
11. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 13.1.
12. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 16.7.
13. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 20.3.

- B. TSX-8500: Exposed use, closed-cell polyisocyanurate insulation with glass fiber

reinforced foil facer on each side. Exposed side of board carries a 1.5 mil reflective aluminum surface.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 25 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.
9. Fire Performance in accordance with UL 1715.
10. Fire Performance in accordance with NFPA 285.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

11. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
12. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.6.
13. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 13.1.
14. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 16.7.
15. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 20.3.
16. Thickness: 3.5 inches (89mm).
  - a. Thermal Resistance (R): 23.9.
17. Thickness: 4.0 inches (102mm).
  - a. Thermal Resistance (R): 27.4.
18. Thickness: 4.5 inches (114mm).
  - a. Thermal Resistance (R): 31.0.

C. TSX-8510: Exposed use, closed-cell polyisocyanurate insulation with glass fiber reinforced foil facer on each side. Exposed side of board carries a 1.5 mil white aluminum surface.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 25 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.
9. Fire Performance in accordance with UL 1715.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

10. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
11. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.6.

12. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 13.1.
13. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 16.7.
14. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 20.3.
15. Thickness: 3.5 inches (89mm).
  - a. Thermal Resistance (R): 23.9.
16. Thickness: 4.0 inches (102mm).
  - a. Thermal Resistance (R): 27.4.
17. Thickness: 4.5 inches (114mm).
  - a. Thermal Resistance (R): 31.0.

D. Thermasheath-SI: Composite product made up of an insulation and structural component. The insulation component is a closed-cell polyisocyanurate insulation with reinforced foil facer on each side. Following physical properties are for the insulation component only.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 75 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

9. Thickness: 0.5 inches (13mm).
  - a. Thermal Resistance (R): 3.2.
10. Thickness: 0.75 inches (19mm).
  - a. Thermal Resistance (R): 5.0.
11. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.

E. Thermasheath-3: Closed-cell polyisocyanurate insulation with reinforced foil facer on each side.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 75 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

9. Thickness: 0.5 inches (13mm).
  - a. Thermal Resistance (R): 3.2.
10. Thickness: 0.75 inches (19mm).
  - a. Thermal Resistance (R): 5.0.

11. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
12. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.6.
13. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 13.1.
14. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 16.7.
15. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 20.3.
16. Thickness: 3.5 inches (89mm).
  - a. Thermal Resistance (R): 23.9.
17. Thickness: 4.0 inches (102mm).
  - a. Thermal Resistance (R): 27.4.
18. Thickness: 4.5 inches (114mm).
  - a. Thermal Resistance (R): 31.0.

F. R-Matte Plus-3: Closed-cell polyisocyanurate insulation with reinforced foil facer on each side; reflective on one side and non-glare matte on the other side.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 75 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

9. Thickness: 0.5 inches (13mm).
  - a. Thermal Resistance (R): 3.2.
10. Thickness: 0.75 inches (19mm).
  - a. Thermal Resistance (R): 5.0.
11. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
12. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.6.
13. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 13.1.
14. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 16.7.
15. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 20.3.
16. Thickness: 3.5 inches (89mm).
  - a. Thermal Resistance (R): 23.9.
17. Thickness: 4.0 inches (102mm).
  - a. Thermal Resistance (R): 27.4.
18. Thickness: 4.5 inches (114mm).
  - a. Thermal Resistance (R): 31.0.

G. Durasheath-3: Closed-cell polyisocyanurate insulation with an inorganic polymer coated glass fiber mat facer on each side.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.



2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 75 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 1.5 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

8. Thickness: 0.5 inches (13mm).
  - a. Thermal Resistance (R): 3.0.
9. Thickness: 0.75 inches (19mm).
  - a. Thermal Resistance (R): 4.5.
10. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
11. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.0.
12. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 12.1.
13. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 15.3.
14. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 18.5.
15. Thickness: 3.5 inches (89mm).
  - a. Thermal Resistance (R): 21.7.
16. Thickness: 4.0 inches (102mm).
  - a. Thermal Resistance (R): 25.0.
17. Thickness: 4.5 inches (114mm).
  - a. Thermal Resistance (R): 28.3.

H. TSP-3 (Thermasheath Plus-3): Closed-cell polyisocyanurate insulation with glass fiber reinforced foil facer on each side.

1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
2. Compressive Strength in accordance with ASTM D1621: 20 psi.
3. Flame Spread in accordance with ASTM E84: 75 or less.
4. Smoke Developed in accordance with ASTM E84: 450 or less.
5. Water Vapor Transmission in accordance with ASTM E96: Less than 0.3 perms.
6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.
8. Air Permeance in accordance with ASTM E2178: Less than 0.02 l/ssm.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

9. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
10. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.6.
11. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 13.1.
12. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 16.7.

13. Thickness: 3.0 inches (76mm).
    - a. Thermal Resistance (R): 20.3.
  14. Thickness: 3.5 inches (89mm).
    - a. Thermal Resistance (R): 23.9.
  15. Thickness: 4.0 inches (102mm).
    - a. Thermal Resistance (R): 27.4.
  16. Thickness: 4.5 inches (114mm).
    - a. Thermal Resistance (R): 31.0.
- I. TSA FA-3: Closed-cell polyisocyanurate insulation with glass fiber / organic mat facer on each side.
1. Density (Nominal) in accordance with ASTM D1622: 2.0 pcf.
  2. Compressive Strength in accordance with ASTM D1621: 20 psi.
  3. Flame Spread in accordance with ASTM E84: 75 or less.
  4. Smoke Developed in accordance with ASTM E84: 450 or less.
  5. Water Vapor Transmission in accordance with ASTM E96: Less than 1.5 perms.
  6. Water Absorption in accordance with ASTM C209: Less than 1 percent by volume.
  7. Dimensional Stability in accordance with ASTM D2126: Less than 2 percent linear change.

**\*\* NOTE TO SPECIFIER \*\* Retain only thicknesses actually required on the project and delete all others.**

8. Thickness: 1.0 inches (25mm).
  - a. Thermal Resistance (R): 6.0.
9. Thickness: 1.5 inches (38mm).
  - a. Thermal Resistance (R): 9.0.
10. Thickness: 2.0 inches (51mm).
  - a. Thermal Resistance (R): 12.1.
11. Thickness: 2.5 inches (64mm).
  - a. Thermal Resistance (R): 15.3.
12. Thickness: 3.0 inches (76mm).
  - a. Thermal Resistance (R): 18.5.
13. Thickness: 3.5 inches (89mm).
  - a. Thermal Resistance (R): 21.7.
14. Thickness: 4.0 inches (102mm).
  - a. Thermal Resistance (R): 25.0.
15. Thickness: 4.5 inches (114mm).
  - a. Thermal Resistance (R): 28.3.

**\*\* NOTE TO SPECIFIER \*\* Retain only insulation types required on the project and delete all others.**

## PART 3 EXECUTION

### 3.1 EXAMINATION

- A. Do not begin installation until substrates have been properly prepared.
- B. If substrate preparation is the responsibility of another installer, notify Architect of unsatisfactory preparation before proceeding.

### 3.2 PREPARATION

- A. Clean surfaces thoroughly prior to installation.
- B. Prepare surfaces using the methods recommended by the manufacturer for

achieving the best result for the substrate under the project conditions.

### 3.3 INSTALLATION

- A. Install in accordance with manufacturer's instructions.

### 3.4 PROTECTION

- A. Protect installed products until completion of project.
- B. Touch-up, repair or replace damaged products before Substantial Completion.

END OF SECTION