

NEUEX MD Medium Duty Fireclay Brick

www.neuex.com

Technical Data

P.C.E. (ASTM C27)	Cone 29-30
Method of Manufacture	Dry Press
Bulk Density	133 lbs./cu.ft.
Modulus of Rupture	1000-1300 PSI
Cold Crushing Strength	3,500-4,500 PSI
Chemical analysis, typical Silica Titanium dioxide Ferric oxide Alumina Alkalies [Na ₂ O + K ₂ O]	59.9% 1.48% 1.97% 32.9% 2.29%
Apparent Porosity	16% - 18%

Note: All data subject to reasonable deviation and should not be used for specification purposes.