

TDS – EcoSoya CB-135

Information

Product Description

EcoSoya CB-135 is formulated for use in the manufacture of container candles.

Physical Properties

Test	Method	Typical Value
Congealing Point, °C	ASTM D938	37.0
Viscosity @ 100°C, cSt	ASTM D445	9.5
Penetration @ 25°C, dmm	BS 1426	45
Colour	Visual	Off White

Statement

- Formulated from materials whose refining history is fully traceable.
- Does not contain or come into contact with any animal or GMO products at any stage of its manufacture
- Does not contain residual solvents as per guidelines CPMP/ICH283/95.
- Has not been tested on animals by ourselves or on our behalf.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users must make their own tests to determine the suitability of these products for their own particular purposes. The company makes no warranty of any kind, expressed or implied, including those of merchantability or fitness for a particular purpose, other than that the material conforms to its applicable current Standard Specifications.