

# Natural NR/SBR


## SPECIFICATION SHEET

<b>Grade</b>	<b>No8</b>	
<b>Colour</b>	<b>BLACK</b>	
<b>Elastomer</b>	<b>NR/SBR</b>	
<b>Quality</b>	<b>ELECTRICALLY TESTED 11KV 450v WORKING FINE FLUTED</b>	
<b>Hardness Shore A ±5</b>	<b>70°</b>	<b>ISO 7619-1</b>
<b>SG (g/cm<sup>2</sup>)</b>	<b>1.5</b>	<b>ISO 2781</b>
<b>Tensile (N/mm<sup>2</sup>)</b>	<b>3.5</b>	<b>ISO 37</b>
<b>Elongation %</b>	<b>300</b>	<b>ISO 37</b>
<b>Compression %</b>		<b>ISO 37</b>
<b>Tear Strength</b>	<b>20</b>	<b>ISO 34-1</b>
<b>Abrasion mm<sup>3</sup></b>	<b>200</b>	<b>ISO 37</b>
<b>Temperature (° C) from</b>		
<b>Temperature (°C) to</b>		

### Roll Tolerances

Width tolerance:	+/- 2%	ISO 3302 SW1
Length tolerance:	+/- 2%	ISO 3302 SW1

### Thicknesses available

6mm	.914m, 1m, 1.22m	
-----	------------------	---

### Thickness

0.5– 1mm	+/- 0.2mm
1.5mm –3mm	+/- 0.3mm
4mm—5mm	+/- 0.4mm
6mm	+/- 0.5mm
8mm	+/- 0.7mm
10mm—15mm	+/- 1mm
20mm	+/- 1.4mm
25mm	+/- 1.75mm

 Items listed above usually ex stock.

**Other thicknesses and sizes available, please contact sales office for your requirements**

### QUALITY ASSURED PRODUCTS WITH FULL TRACEABILITY

Care should be taken in selecting the most suitable quality for each application.  
Advice is available but final responsibility remains with the customer.